PCT WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification 4 :		(11) International Publication Number:
C03C 13/00, 13/02, 25/06	A2	WO 89/12032
		(43) International Publication Date: 14 December 1989 (14.12.89)

(21) International Application Number: PCT/US89/02288

(22) International Filing Date: 25 May 1989 (25.05.89)

(30) Priority data:
201,513 1 June 1988 (01.06.88) US

(71) Applicant: MANVILLE SALES CORPORATION [US/US]; Manville Plaza, 5th Floor, P.O. Box 5108, Denver, CO 80217 (US).

(72) Inventors: OLDS, Leonard, Elmo ; 977 South Lake Gulch Road, Castle Rock, CO 80104 (US). KIELMEYER, William, Henry ; 3374 West Chenango Avenue, Englewood, CO 80110 (US).

(74) Agent: SCHRAMM, William, J.; Brooks & Kushman, 2000 Town Center, Suite 2000, Southfield, MI 48075 (US).

(81) Designated States: AT (European patent), AU, BE (European patent), BR, CH (European patent), DE (European patent), DK, FI, FR (European patent), GB (European patent), IT (European patent), JP, KP, KR, LU (European patent), NL (European patent), NO, SE (European patent).

Published
Without international search report and to be republished upon receipt of that report.

(54) Title: PROCESS FOR DECOMPOSING AN INORGANIC FIBER

(57) Abstract

Inorganic fibers which have a silicon extraction of greater than 0.02 wt% Si/day in physiological saline solutions. The fiber contains SiO_2, MgO, CaO, and at least one of Al_2O_3, ZrO_2, TiO_2, B_2O_3, iron oxides, or mixtures thereof. Also disclosed are inorganic fibers which have diameters of less than 3.5 microns and which pass the ASTM E-119 two hour fire test when processed into a fiber blanket having a bulk density in the range of about 1.5 to 3 pcf.

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	FI	Finland	ML	Mali
AU	Australia	FR	France	MR	Mauritania
BB	Barbados	GA	Gabon	MW	Malawi
BE	Belgium	GB	United Kingdom	NL	Netherlands
BF	Burkina Fasso	HU	Hungary	NO	Norway
BG	Bulgaria	IT	Italy	RO	Romania
BJ	Benin	JP	Japan	SD	Sudan
BR	Brazil	KP	Democratic People's Republic of Korea	SE	Sweden
CF	Central African Republic			SN	Senegal
CG	Congo	KR	Republic of Korea	SU	Soviet Union
CH	Switzerland	LI	Liechtenstein	TD	Chad
CM	Cameroon	LK	Sri Lanka	TG	Togo
DE	Germany, Federal Republic of	LU	Luxembourg	US	United States of America
DK	Denmark	MC	Monaco		
ES	Spain	MG	Madagascar		

PROCESS FOR DECOMPOSING AN INORGANIC FIBER

FIELD OF INVENTION

This invention relates to inorganic fiber compositions and more particularly it relates to inorganic fiber compositions which can contain silica, magnesia, calcium oxide, alumina, and other oxides. Some of the inventive fibers have excellent fire ratings, some have especially low durabilities in physiological saline solutions, and some have combinations of these foregoing properties.

BACKGROUND OF THE INVENTION

For many years, inorganic fibers generically referred to in the industry as "mineral wool fibers", made from slag, rock, fly ash, and other by-product raw materials have been manufactured. These fibers have been typically manufactured by melting the slag, rock, etc., containing such oxides as silica, alumina, iron oxide (ferrous and ferric), calcium oxide, and magnesia; allowing the molten material to be blown by gas or steam or to impinge on rotors at high speeds; and causing the resulting blown or spun fibers to be accumulated on a collecting surface. These fibers are then used in bulk or in the form of mates, blankets, and the like as both low and high temperature insulation. U.S. Patent No. 2,576,312 discloses a conventional mineral wool composition and method for making the same.

In the past, the industry has well recognized the standard drawbacks associated with conventional mineral wool fibers. Conventional mineral wool fibers may have high contents of undesired oxides which often

detract from their refractory properties. The conventional mineral wools are coarse, i.e. they have average fiber diameters of 4 to 5 microns (measured microscopically) and have high shot contents in the range of 30 to 50 weight percent. The coarseness of the fiber reduces the insulating value of the fiber and makes conventional mineral wool unpleasant to handle and unfriendly to the touch. For example, because of their coarse fiber diameters, conventional mineral wool blankets must have bulk densities of from 4 to 8 pcf and even higher in order to pass the ASTM E-119 two hour fire test. On the other hand, fiber glass blankets are often made with bulk densities of 2 pcf or lower. While the fiber glass blankets are friendly because of their low bulk densities and relatively fine fiber diameter, they do not have sufficient fire resistance so as to pass even the one hour ASTM E-119 fire test.

Recently, another potential problem with traditional mineral wool and other types of fiber has been recognized. It is well known that inhalation of certain types of fiber can lead to elevated incidence of respiratory disease, including cancers of the lung and surrounding body tissue. Several occurrences are well-documented in humans for several types of asbestos fiber. Although for other varieties of natural and manmade mineral fiber direct and unequivocal evidence for respiratory disease is lacking, the potential for such occurrence has been inferred from results of tests on laboratory animals. In the absence or insufficiency of direct human epidemiological data, results from fiber inhalation or implantation studies on animals provides the best "baseline information" from which to extrapolate disease potential.

Chronic toxicological studies on animals have, however, been able to statistically demonstrate the importance of three key factors that relate directly to the potential for respiratory disease and especially carcinoma: (a) dose of fiber received (including time of exposure); (b) dimension of the inhaled fiber; and (c) persistence of the fiber within the lung. The effects of dose and dimension have been well-characterized from such studies and as a result are fairly well known in regard to human disease potential. The dose is obviously a product of the environment in which the fiber is used and the manner in which it is used. The dimension and persistence of the fiber within the lung, on the other hand, are functions of the manner in which the fiber is formed and of its chemical composition. In general, the smaller the fiber the more likely that it will become embedded in lung tissue when inhaled, thus increasing the danger of respiratory disease.

Although less is known about the link between persistence of the fiber within the lung and respiratory disease, increasing attention is being focused on this aspect of the health issue. Biological persistence refers to the length of time a fiber endures as an entity within the body. The physiochemical concept that most closely relates to persistence and is perhaps more easily quantified is that of "durability" - specifically, the chemical solubility (or resistance to solubility) of fibers in body fluids and the tendency of such fibers to maintain physical integrity within such an environment. In general, the less durable a fiber is, the less will be the potential health risk associated with the inhalation of that fiber. One method of measuring the chemical durability of a fiber in body fluids is to measure its durability in physiological

saline solutions. This can be done by quantifying the rate of extraction of a chemical component of the fiber such as silicon into the physiological saline solution over a certain period of time.

Thus, as can be easily concluded from the foregoing discussion, conventional mineral wool fibers have several serious drawbacks. However, even the alternatives to mineral wools have problems. For example, as mentioned earlier glass fibers have a fire resistance problem and whereas the refractory ceramic fibers have been gaining increasing use in recent years as an alternative to mineral wool fibers because of their ultra-high temperature resistance and superior ability to pass all fire rating tests, their use is limited by the fact that they are relatively expensive and have a relatively high chemical durability in physiological saline solutions as well.

In conclusion, there is a great need in the industry for low cost, friendly feeling low bulk density inorganic fibers which have good fire resistance properties as measured by their ability to pass the ASTM E-119 two hour fire test. Additionally, there is a tremendous demand for fibers which have especially low durabilities in physiological saline solutions. What would be particularly advantageous to the industry would be fibers with combinations of the above mentioned sought after properties. Also, advantageous would be fibers which also have excellent refractory properties as well, e.g. high continuous service temperatures.

SUMMARY OF THE INVENTION

In one embodiment of the present invention, there are provided inorganic fibers having a silicon extraction of greater than about 0.02 wt% Si/day in physiological saline solutions and a composition consisting essentially of about 0-10 wt% of either Al_2O_3, ZrO_2, TiO_2, B_2O_3, iron oxides, or mixtures thereof; 35-70 wt% SiO_2; 0-50 wt% MgO; and CaO.

In another embodiment of the present invention, there are provided inorganic fibers which have a 5 hour silicon extraction in physiological saline solutions of at least about 10 ppm. These fibers can broadly have compositions consisting essentially of the following ingredients at the indicated weight percentage levels:

0-1.5 wt% of either Al_3O_3, ZrO_2, TiO_2, B_2O_3, iron oxides, or mixtures thereof; 40-70 wt% SiO_2; 0-50 wt% MgO; and CaO

1.5-3 wt% of either Al_2O_3, ZrO_2, TiO_2, B_2O_3, iron oxides, or mixtures thereof; 40-66 wt% SiO_2; 0-50 wt% MgO; and CaO

3-4 wt% of either Al_2O_3, ZrO_2, TiO_2, B_2O_3, iron oxides, or mixtures thereof; 40-64 wt% SiO_2; 0-50 wt% MgO; and CaO

4-6 wt% of either Al_2O_3, ZrO_2, TiO_2, B_2O_3, iron oxides, or mixtures thereof; 40-59 wt% SiO_2; 0-25 wt% MgO; and CaO

6-8 wt% of either Al_2O_3, ZrO_2, TiO_2, B_2O_3, iron oxides, or mixtures thereof; 35-54 wt% SiO_2; 0-25 wt% MgO; and CaO

8-10 wt% of either Al_2O_3, ZrO_2, TiO_2, B_2O_3, iron oxides, or mixtures thereof; 35-45 wt% SiO_2; 0-20 wt% MgO; and CaO

In a preferred embodiment, inventive fibers with 5 hour silicon extractions of greater than about 20 ppm and most preferably greater than about 50 ppm are provided.

In another embodiment of the present invention there are provided inorganic fibers having a diameter of less than 3.5 microns and which pass the ASTM E-119 two hour fire test when processed into a fiber blanket having a bulk density in the range of about 1.5 to 3 pcf and having a composition consisting essentially of about: 0-10 wt% of either Al_2O_3, ZrO_2, TiO_2, B_2O_3, iron oxides, or mixtures thereof; 58-70 wt% SiO_2; 0-21 wt% MgO; 0-2 wt% alkali metal oxides; and CaO and wherein the amount of alumina + zirconia is less than 6 wt% and the amount of iron oxides or alumina + iron oxides is less than 2 wt%. Preferably, the inventive fibers in this embodiment may have compositions consisting essentially of about:

0-1.5 wt% of either Al_2O_3, ZrO_2, TiO_2, B_2O_3, iron oxides, or mixtures thereof; 58.5-70 wt% SiO_2; 0-21 wt% MgO; 0-2 wt% alkali metal oxides; and CaO

greater than 1.5 wt% up to and including 3 wt% of either Al_2O_3, ZrO_2, TiO_2, B_2O_3, iron oxides, or mixtures thereof; 58.5-66 wt% SiO_2; 0-21 wt% MgO; 0-2 wt% alkali metal oxides; and CaO

greater than 3 wt% up to and including 4 wt% of either Al_2O_3, ZrO_2, TiO_2, B_2O_3, iron oxides, or mixtures thereof; 58-63 wt% SiO_2; 0-8 wt% MgO; 0-2 wt% alkali metal oxides; and CaO

greater than 4 wt% up to and including 6 wt% of either Al_2O_3, ZrO_2, TiO_2, B_2O_3, iron oxides, or mixtures thereof; 58-59 wt% SiO_2; 0-7 wt% MgO; 0-2% alkali metal oxides; and CaO.

As discussed herein earlier, there has been a demand in the industry for inorganic fibers with an excellent fire rating at low bulk densities and fibers with especially low chemical durabilities in physiological saline solutions. Therefore, each category of inventive fibers should fulfill a real need in the industry and should be available for applications where heretofore low cost, mineral wool type fibers have not been available. What is particularly advantageous about the present invention is the fact that fibers are provided where a special demand exists, i.e. applications in the industry where fibers with both an excellent fire rating and an especially low durability in physiological saline solutions are in demand.

Other features and aspects, as well as the various benefits and advantages, of the present invention will be made clear in the more detailed description which follows.

DETAILED DESCRIPTION OF THE INVENTION

The inventive fiber compositions of the present invention can be made from either pure metal oxides or less pure raw materials which contain the desired metal oxides. Table 1 herein gives an analysis of some of the various raw materials which can be used to make inventive fiber compositions. Physical variables of the raw materials such as particle size may be chosen on the basis of cost, handleability, and similar considerations.

Except for melting, the inventive fibers are formed in conventional inorganic fiber forming equipment

and by using standard inorganic fiber forming techniques as known to those skilled in the art. Preferably, production will entail electric furnace melting rather than cupola melting since electric melting keeps molten oxides of either pure or less pure raw materials more fully oxidized thereby producing longer fibers and stronger products. The various pure oxides or less pure raw materials are granulated to a size commonly used for electric melting or they may be purchased already so granulated.

The granulated raw materials are then mixed together and fed to an electric furnace where they are melted by electric resistance melting with electrodes preferably positioned according to the teachings of U.S. Patent No. 4,351,054. Melt formation can be either continuous or batchwise although the former is preferred. The molten mixture of oxides is then fiberized as disclosed in U.S. Patent No. 4,238,213.

While the fiberization techniques taught in U.S. 4,238,213 are preferred for making the inventive fibers, other conventional methods may be employed such as sol-gel processes and extrusion through holes in precious metal alloy baskets.

The fibers so formed will have lengths in the range of from about 0.5 to 20 cm and diameters in the range of from about 0.05 to 10 microns with the average fiber diameter being in the range of about 1.5 to 3.5 microns. Table 2 shows the average fiber diameter (measured microscopically) and the unfiberized shot content of various inventive fibers. As may be seen, the average microscopic fiber diameter was 2.3 microns and the average unfiberized shot content was 27%.

For purposes of comparison, conventional mineral wool fibers were also tested with the results being given in Table 2 as numbers 226 and 229. These conventional fibers averaged 4.7 microns (measured microscopically) in diameter and had an average 40 wt% shot content. The continuous service temperature ranged from 1370°F to 1490°F, averaging 1420°F.

Table 3 contains an extensive chemical analysis of a number of inventive fibers. Because of the large number of fiber samples containing alumina additives made to the base calcium oxide/magnesia/silica system, only the average analysis of the minor constituent of these fibers are given in Table 3. The silica, alumina, magnesia, and calcium oxide contents for these fibers are given in Table 4.

As used herein, the "service temperature" of an inorganic fiber is determined by two parameters. The first is the obvious condition that the fiber must not soften or sinter at the temperature specified. It is this criterion which precludes the use of glass fibers at temperatures about 800°F to 1000°F (425° to 540°C). Additionally, a felt or blanket made from the fibers must not have excessive shrinkage when soaking at its service temperature. "Excess shrinkage" is usually defined to be a maximum of 5% linear or bulk shrinkage after prolonged exposure (usually for 24 hours) at the service temperature. Shrinkage of mats or blankets used as furnace liners and the like is of course a critical feature, for when the mats or blankets shrink they open fissures between them through which the heat can flow, thus defeating the purpose of the insulation. Thus, a fiber rated as a "1500°F (815°C) fiber" would be defined

as one which does not soften or sinter and which has acceptable shrinkage at that temperature, but which begins to suffer in one or more of the standard parameters at temperatures above 1500°F (815°C).

The service temperatures for a representative number of fibers in the inventive compositional range are listed in Table 2. The continuous service temperature for constant silica/magnesia/calcium oxide ratios are given in Table 6. As may be seen in all cases, the lower the alumina content of the fiber, the higher the service temperature will be, with the highest service temperature being at zero percent alumina for alumina contents less than 30%. Thus to attain the most desired properties of the inventive fiber it is not possible to accept any of the alumina contents resulting from melting the traditional mineral wool raw materials. Rather, various amounts of sufficiently pure oxides will be required to dilute the alumina contents to the desired low levels. To attain fibers of the highest service temperatures, only pure raw materials with essentially no significant amounts of alumina must be used.

A series of inventive fibers were also tested for their silicon extraction in a saline solution according to the following procedure:

A buffered model physiological saline solution was prepared by adding to 6 liters of distilled water the following ingredients at the indicated concentrations:

Ingredient	Concentration, g/l
$MgCl_2 6H_2O$	0.160
NaCl	6.171

KCl	0.311
Na_2HPO_4	0.149
Na_2SO_4	0.079
$CaCl_2 2H_2O$	0.060
$NaHCO_3$	1.942
$NaC_2H_3O_2$	1.066

Before testing, this solution was buffered to a pH of 7.6 by bubbling with a gaseous mixture of 5% CO_2/95%N_2.

One half (1/2) gram of each sample of fiber listed in Table 3 was then placed into separate closed, plastic bottles along with 50 cc of the prepared physiological saline solution and put into an ultrasonic bath for 5 hours. The ultrasonic vibration application was adjusted to give a temperature of 104°F at the end of the 5 hour period. At the end of the test period, the saline solution was filtered and the solution chemically analyzed for silicon content. The silicon concentration in the saline solution was taken to be a measure of the amount of fiber which solubilized during the 5 hour test period. The CaO and MgO contents of the fiber were similarly solubilized.

One of the inventive fibers was tested for silicon extraction in a physiological saline solution for periods of up to 6 months. Results were as follows:

Fiber Number	Silicon Extraction in 6 Months	Steady State Silicon Extraction Rate For 0.20 m^2/g Surface Area, % Si/day	Total Amphoteric Oxides in Fiber	Comments On Fiber Residue After 6 Months
29 (inventive)	96%	0.16%	1.0%	carbonate hydroxyl apatite fiber, disintegrated into small particles
137 (non-inventive)	3%	0.013%	8.9%	slight fine grained fibers with uniform corrosion
235 (non-inventive)	4%	0.012%	25.6%	no fiber corrosion; some surface deposition

Categorization of oxides melts according to scales of acidity or basicity has been well known for many years. (See "A Scale of Acidity and Basicity in Glass," Glass Industry, February 1948, pp 73-74.) We have now found that by strictly controlling the compositions of the oxide melts according to the acidic or basicity behavior of the respective oxides, fibers can be made which are surprisingly soluble in saline solutions. Increasing the content of silica, alumina, and the amphoteric oxides in the fiber increases the acid ratio of the fiber composition. This tends to stabilize the system against silicon extraction by weak solutions as a result of relative changes in the interatomic bonding forces and extension of the silica network. Other amphoteric oxides besides alumina will have an alumina equivalency with respect to extraction by saline solutions. The amphoteric oxides zirconia and titania appear to have an alumina equivalency of close to 1 to 1. We have found that in general for desired high saline solubility the amount of total amphoteric oxides must be kept below about 10% depending upon the amount of silica present. On the other hand, with the exception of iron and manganese oxides, the basic oxides can vary widely since their alumina equivalency is small. However, while iron and manganese oxides are generally considered to be basic in nature, their behavior with respect to saline solubility more closely relate to the amphoteric oxides, thus the amounts of iron and manganese oxides must be similarly limited.

Many of the fibers were tested for their fire resistance according to the following simulated fire rating test procedure:

For screening test purposes, a small furnace was constructed using an electrically heated flat-plate element at the back of the heat source. A 6 inch x 6 inch x 2 inch thick sample of 1 3/4 to 6 1/2 pcf density of each formulated fiber was mounted parallel with the element and 1 inch from it. Thermocouples were then positioned at the center of the fiber sample surfaces. A computer was used to control power via a simple on-off relay system to the heating element. The position of the relay was based on the reading of the thermocouple on the sample surface nearest the element and the programmed fire test heat-up schedule.

The furnace was heated so as to follow a standard ASTM E-119 time/temperature curve for the 2-hour test period. In the test utilized herein, failure of the fiber is considered to occur when the furnace is unable to maintain the standard temperature per ASTM E-119 because the fiber insulation has sintered sufficiently to allow heat to escape through the fiber layer.

The results of the testing of the fibers for saline solubility and the two hour ASTM E-119 fire test are given in Table 4 for the fibers made with alumina addition and in Table 5 for the remaining fibers to which other oxidic constituents were added. These additions included: B_2O_3, P_2O_5, TiO_2, ZrO_2, Fe_2O_3 + MnO, La_2O_3, Cr_2O_3, and Na_2O. For glass fibers within the scope of the invention to function in an ASTM E-119 fire test, i.e. to withstand the rising temperatures of a simulated fire which can reach 1850°F in two hours, it is necessary that they convert from an amorphous condition to a beneficial pseudo crystalline state during heat-up. The inventive fibers do this but can be assisted in this function by the inclusion of suitable crystal nucleating

agents. Such agents may include TiO_2, ZrO_2, platinum, Cr_2O_3, P_2O_5, and others. Such additions are within the scope of this invention.

TABLE 1
RAW MATERIALS USED

	Pure Raw Materials				
	Silica Sand	Quick Lime	Calcined Dolomite	Aluminum Oxide	Magnesium Oxide
ACIDIC OXIDES					
SiO2	99.0	0.34	0.50	0.02	0.4
AMPHOTERIC OXIDES					
TiO_2	nil	nil	nil	0.002	nil
Al_2O_3	0.30	0.26	0.50	98.8	0.1
BASIC OXIDES					
Fe_2O_3	0.30	0.05	0.15	0.02	0.7
MnO	--	--	--	--	--
MgO	0.02	0.14	40.0	nil	96.3
CaO	0.03	97.75	57.0	0.01	2.0
Na_2O	0.04	0.02	0.01	0.30	0.02
K_2O	0.01	0.01	nil	0.01	0.01
MISCELLANEOUS					
SO_3	--	--	0.4	--	--
$S^=$	--	--	--	--	--
C	--	--	--	--	--
LOI	0.2	0.7	3.0	0.20	1.8
TOTAL	99.90	99.27	101.56	99.36	101.33

TABLE 1
RAW MATERIALS USED (continued)

	Less Pure Raw Materials			
	Kaolin	Blast Furnace Slag	Nepheline Syenite	Talc
CIDIC OXIDES				
SiO_2	50.5	35.16	61.3	61.2
MPHOTERIC OXIDES				
TiO_2	1.61	0.62	0.003	nil
Al_2O_3	43.6	12.88	23.4	0.7
ASIC OXIDES				
Fe_2O_3	0.80	0.20	0.07	0.85
MnO	--	0.62	--	--
MgO	0.01	16.06	0.05	31.7
CaO	0.04	32.94	0.58	0.19
Na_2O	0.06	0.45	9.60	--
K_2O	0.02	0.25	4.50	--
SCELLANEOUS				
SO_3	--	0.28	--	--
$S^=$	--	1.03	--	--
C	--	0.30	--	--
I	2.90	--	0.62	5.0
TAL	99.54	100.79	100.12	99.0

Silica Sand: Ottawa Silica - Sil-co-Sil Grade 295
Quick Lime: Mississippi Lime - Pulverized Quick Lime
Calcined Dolomite: Ohio Lime NO. 16 Burnt Dolomitic Lime
Aluminum Oxide: Reynolds Calcined Alumina, RC-23
Magnesium Oxide: Baymag 56 Feed Grade
Kaolin: American Cyanamide Andersonville Kaolin
Blast Furnace Slag: Calumite Morrisville Slag
Nepheline Syenite: Indusmin Grad A400
Talc: Pfizer Grade MP4426

Additives:
Soda Ash: 58.3% Na_2O
Boric Acid: 55.5% B_2O_3
Magnetite Iron Concentrates: 98.5% Iron Oxides
Zircon: 66.2% ZrO_2
Manganese Oxide: 99% MnO_2
Titanium Dioxide: 99% TiO_2
Chromium Oxide: 99.5% Cr_2O_3
Lanthanum Carbonate: Moly Corp.

TABLE 3
COMPOSITION OF FIBERS

TEST NO.	ACIDIC OXIDES				AMPHOTERIC OXIDES			
	B_2O_3	SiO_2	P_2O_5	SUB TOTAL	TiO_2	Al_2O_3	ZrO_2	SUB TOTAL
Composition of Fibers with Al_2O_3 additions (minor constituents only)								
1 to	0.00	--	0.00	--	0.01	--	0.01	0.02
	--	--	--	--	--	--	--	--
Composition of Fibers with B_2O_3 additions								
164	0.32	64.8	--	65.12	--	0.06	--	0.06
165	0.52	63.9	--	64.42	--	1.20	--	1.20
166	0.64	64.6	--	65.24	--	0.06	--	0.06
167	0.82	64.5	--	65.32	--	0.06	--	0.06
168	1.33	64.1	--	65.43	--	0.06	--	0.06
169	1.37	64.1	--	65.47	--	0.06	--	0.06
170	2.22	63.6	--	65.82	--	0.06	--	0.06
171	8.41	59.6	--	68.01	--	0.06	--	0.06
Composition of Fibers with P_2O_5 additions								
2	--	49.6	6.05	55.65	0.06	0.38	0.04	0.48
Composition of Fibers with TiO_2 additions								
173	--	48.6	--	48.6	10.0	41.4	--	51.4
Composition of Fibers with ZrO_2 additions								
174	--	63.5	--	63.5	.01	0.88	0.21	1.10
175	--	59.2	--	59.2	--	0.33	0.40	0.73
176	--	59.5	--	59.5	--	0.31	0.42	0.73

TABLE 3
COMPOSITION OF FIBERS (continued)

TEST NO.	BASIC OXIDES FeO_3	MnO	La_2O_3	Cr_2O_3	MgO	Li_2O	CaO	BaO	Na_2O	K_2O	SUB TOTAL
Composition of Fibers with Al_2O_3 additions (minor constituents only)											
1 to	0.06	0.02	0.00	0.02	--	0.00	--	0.04	0.04	0.01	.19
	--	--	--	--	--	--	--	--	--	--	
Composition of Fibers with B_2O_3 additions											
164	--	--	--	--	8.7	--	26.6	--	--	--	35.3
165	--	--	--	--	8.6	--	26.2	--	--	--	34.8
166	--	--	--	--	8.7	--	26.5	--	--	--	35.2
167	--	--	--	--	8.7	--	26.5	--	--	--	35.2
168	--	--	--	--	8.6	--	26.3	--	--	--	34.9
169	--	--	--	--	8.6	--	26.3	--	--	--	34.9
170	--	--	--	--	8.5	--	26.1	--	--	--	34.6
171	--	--	--	--	8.0	--	24.0	--	--	--	32.0
Composition of Fibers with P_2O_5 additions											
2	0.21	0.00	--	0.68	11.15	0.00	31.45	0.00	0.05	0.04	43.58
Composition of Fibers with TiO_2 additions											
173	--	--	--	--	--	--	--	--	--	--	--
Composition of Fibers with ZrO_2 additions											
174	--	--	--	--	0.33	--	35.55	--	.03	.01	35.92
175	--	--	--	--	0.41	--	39.1	--	--	--	39.51
176	--	--	--	--	0.42	--	39.1	--	--	--	39.52

TABLE 3
COMPOSITION OF FIBERS (continued)

TEST NO.	SO_3	MISCELLANEOUS Misc.	SUB TOTAL	TOTAL
Composition of Fibers with Al_2O_3 additions (minor constituents only)				
1 to	.05/	.02	.07/	.14
	.20	--	.22	.44
Composition of Fibers with B_2O_3 additions				
164	--	--	--	100.48
165	--	--	--	100.42
166	--	--	--	100.5
167	--	--	--	100.58
168	--	--	--	100.39
169	--	--	--	100.43
170	--	--	--	100.48
171	--	--	--	100.07
Composition of Fibers with P_2O_5 additions				
2	--	0.02	0.02	99.73
Composition of Fibers with TiO_2 additions				
173	--	--	--	100.0
Composition of Fibers with ZrO_2 additions				
174	--	--	--	100.52
175	--	--	--	99.44
176	--	--	--	99.75

TABLE 3
COMPOSITION OF FIBERS

TEST NO.	ACIDIC OXIDES B_2O_3	SiO_2	P_2O_5	SUB TOTAL	AMPHOTERIC OXIDES TiO_2	Al_2O_3	ZrO_2	SUB TOTAL
Composition of Fibers with ZrO_2 additions (Cont.)								
177	--	59.7	--	59.7	--	0.34	0.50	0.84
8	--	60.0	--	60.0	--	0.36	0.54	0.90
179	--	59.2	--	59.2	--	0.35	0.58	0.93
180	--	54.3	--	54.3	.01	1.29	0.58	1.88
181	--	59.2	--	59.2	--	0.32	0.83	1.15
182	--	46.85	--	46.85	.02	2.03	0.84	2.89
182(a)	--	59.4	--	59.4	--	0.38	2.31	2.69
183	--	59.05	--	59.05	--	0.30	2.65	2.95
184	--	57.96	--	57.96	--	0.42	3.11	3.53
185	--	57.8	--	57.80	--	0.56	3.12	3.68
186	--	59.05	--	59.05	--	0.38	3.27	3.65
187	--	56.88	--	56.88	--	0.32	3.30	3.62
188	--	57.7	--	57.7	--	0.20	3.30	3.50
189	--	58.19	--	58.19	--	0.39	3.36	3.75
190	--	57.86	--	57.86	--	0.36	3.37	3.73
191	--	58.6	--	58.6	--	0.58	3.67	4.25
192	--	58.4	--	58.4	--	0.65	3.69	4.34
193	--	56.65	--	56.65	.02	3.35	4.50	7.87

TABLE 3
COMPOSITION OF FIBERS (continued)

TEST NO.	BASIC OXIDES										SUB TOTAL
	FeO_3	MnO	La_2O_3	Cr_2O_3	MgO	Li_2O	CaO	BaO	Na_2O	K_2O	
Composition of Fibers with ZrO_2 additions (Cont.)											
177	--	--	--	--	0.46	--	38.7	--	--	--	39.16
8	--	--	--	--	0.48	--	38.3	--	--	--	38.78
179	--	--	--	--	0.98	--	37.0	--	--	--	37.98
180	.09	.01	--	--	10.20	--	32.75	.01	.04	.02	43.12
181	--	--	--	--	1.13	--	36.6	--	--	--	37.73
182	.08	.01	--	--	20.6	--	29.2	.03	.05	.01	49.98
182(a)	--	--	--	--	2.06	--	34.9	--	--	--	36.96
183	.06	.00	--	.05	3.08	--	34.84	.00	.03	.01	38.07
184	--	--	--	--	3.55	--	35.17	--	--	--	38.72
185	--	--	--	--	3.74	--	34.4	--	--	--	38.14
186	--	--	--	--	2.57	--	36.94	--	--	--	39.51
187	--	--	--	--	4.00	--	36.45	--	--	--	40.45
188	--	--	--	--	3.00	--	36.0	--	--	--	39.0
189	--	--	--	--	3.26	--	35.39	--	--	--	38.65
190	--	--	--	--	3.22	--	35.66	--	--	--	38.88
191	--	--	--	--	2.72	--	33.5	--	--	--	36.22
192	--	--	--	--	2.59	--	33.2	--	--	--	35.79
193	.05	.00	--	.00	3.35	--	31.9	.00	.05	.01	35.36

TABLE 3
COMPOSITION OF FIBERS (continued)

TEST NO.	MISCELLANEOUS SO_3	Misc.	SUB TOTAL	TOTAL
Composition of Fibers with ZrO_2 additions (Cont.)				
177	--	--	--	99.70
8	--	--	--	99.68
179	--	--	--	98.11
180	--	.01	.01	99.31
181	--	--	--	98.08
182	--	.02	.02	99.74
182(a)	--	--	--	99.05
183	--	.02	.02	100.09
184	--	--	--	100.21
185	--	--	--	99.62
186	--	--	--	102.21
187	--	--	--	100.95
188	--	--	--	100.20
189	--	--	--	100.59
190	--	--	--	100.47
191	--	--	--	99.07
192	--	--	--	98.53
193	--	.01	.01	99.89

TABLE 3
COMPOSITION OF FIBERS

TEST NO.	ACIDIC OXIDES				AMPHOTERIC OXIDES			
	B_2O_3	SiO_2	P_2O_5	SUB TOTAL	TiO_2	Al_2O_3	ZrO_2	SUB TOTAL
Composition of Fibers with FeO_3 and MnO additions								
194	--	64.9	--	64.9	--	0.06	--	0.06
195	--	49.8	--	49.8	.01	18.0	.01	18.02
196	--	50.4	--	50.4	.03	7.45	.01	7.49
197	--	64.34	--	64.34	--	0.06	--	0.06
198	--	63.70	--	63.70	--	1.20	--	1.20
199	--	63.54	--	63.54	--	1.20	--	1.20
200	--	38.9	--	38.9	.01	6.70	.01	6.72
201	--	64.3	--	64.3	--	0.06	--	0.06
202	--	44.6	--	44.6	.01	0.92	.01	0.94
203	--	63.3	--	63.3	--	1.15	--	1.15
204	--	63.6	--	63.6	--	0.06	--	0.06
205	--	43.8	--	43.8	.01	15.26	.01	15.28
206	--	62.3	--	62.3	--	1.20	--	1.20
207	--	63.3	--	63.3	--	0.06	--	0.06
208	--	43.9	--	43.9	.01	14.3	.01	14.32
209	--	62.0	--	62.0	--	0.06	--	0.06
210	--	60.0	--	60.0	--	2.0	--	2.0
211	--	60.0	--	60.0	--	--	--	--

TABLE 3
COMPOSITION OF FIBERS (continued)

TEST NO.	BASIC OXIDES										SUB TOTAL
	FeO_3	MnO	La_2O_3	Cr_2O_3	MgO	Li_2O	CaO	BaO	Na_2O	K_2O	
Composition of Fibers with FeO_3 and MnO additions											
194	0.06	--	--	--	8.72	--	26.6	--	--	--	35.38
195	.22	--	--	--	0.2	--	31.5	--	--	--	31.92
196	.48	.04	--	--	15.2	--	26.2	--	.07	.05	42.04
197	.50	--	--	--	7.80	--	26.4	--	--	--	34.7
198	.69	--	--	--	7.73	--	25.30	--	--	--	33.72
199	.72	--	--	--	7.70	--	25.04	--	--	--	33.46
200	.80	--	--	--	16.1	--	37.5	--	--	--	54.40
201	.96	--	--	--	8.6	--	26.4	--	--	--	35.96
202	1.02	--	--	--	18.1	--	32.8	--	--	--	51.92
203	1.61	--	--	--	7.98	--	25.4	--	--	--	34.99
204	1.92	--	--	--	8.6	--	26.1	--	--	--	36.62
205	2.90	.04	--	.14	22.7	--	15.05	--	.10	.01	40.94
206	3.05	--	--	--	8.0	--	25.0	--	--	--	36.05
207	3.45	--	--	--	8.0	--	25.5	--	--	--	36.95
208	3.50	--	--	--	24.4	--	13.7	--	--	--	41.6
209	4.81	--	--	--	8.0	--	25.5	--	--	--	38.31
210	--	8.0	--	--	30.0	--	--	--	--	--	38.0
211	--	20.0	--	--	20.0	--	--	--	--	--	40.0

TABLE 3
COMPOSITION OF FIBERS (continued)

TEST NO.	MISCELLANEOUS SO_3	Misc.	SUB TOTAL	TOTAL
Composition of Fibers with FeO_3 and MnO additions				
194	--	--	--	100.34
195	.05	.02	.07	99.81
196	.05	.02	.07	100.00
197	--	--	--	99.1
198	--	--	--	98.62
199	--	--	--	98.20
200	.05	.02	.07	100.09
201	--	--	--	100.32
202	--	--	--	97.46
203	--	--	--	99.44
204	--	--	--	100.28
205	.05	.08	.13	100.15
206	--	--	--	99.55
207	--	--	--	100.31
208	--	--	--	99.82
209	--	--	--	100.37
210	--	--	--	100.0
211	--	--	--	100.0

TABLE 3
COMPOSITION OF FIBERS

TEST NO.	ACIDIC OXIDES B_2O_3	SiO_2	P_2O_5	SUB TOTAL	AMPHOTERIC OXIDES TiO_2	Al_2O_3	ZrO_2	SUB TOTAL
Composition of Fibers with La_2O_3 additions								
--	--	58.1	--	58.1	--	0.06	--	0.06
213	--	57.8	--	57.8	--	0.06	--	0.06
214	--	57.5	--	57.5	--	0.06	--	0.06
215	--	56.9	--	56.9	--	0.06	--	0.06
Composition of Fibers with Cr_2O_3 additions								
216	--	62.6	--	62.6	0.01	0.49	0.01	0.51
Composition of Fibers with Na_2O additions								
17	--	64.7	--	64.7	--	0.06	--	0.06
218	--	64.5	--	64.5	--	0.06	--	0.06
219	--	64.4	--	64.4	--	0.06	--	0.06
220	--	63.5	--	63.5	--	1.20	--	1.20
221	--	64.3	--	64.3	--	0.06	--	0.06
222	--	64.2	--	64.2	--	0.06	--	0.06
223	--	64.0	--	64.0	--	0.06	--	0.06
224	--	63.0	--	63.0	--	0.06	--	0.06
225	--	60.3	--	60.3	--	0.06	--	0.06

TABLE 3
COMPOSITION OF FIBERS (continued)

TEST NO.	BASIC OXIDES										SUB TOTAL
	FeO_3	MnO	La_2O_3	Cr_2O_3	MgO	Li_2O	CaO	BaO	Na_2O	K_2O	
Composition of Fibers with La_2O_3 additions											
--	0.16	--	0.00	--	4.60	--	36.71	--	--	--	41.47
213	0.15	--	0.56	--	4.58	--	36.53	--	--	--	41.82
214	0.15	--	0.72	--	4.55	--	36.3	--	--	--	41.72
215	0.15	--	0.92	--	4.51	--	36.0	--	--	--	41.58
Composition of Fibers with Cr_2O_3 additions											
216	0.08	.00	--	0.09	2.30	--	34.10	0.00	0.03	0.01	36.61
Composition of Fibers with Na_2O additions											
17	--	--	--	--	8.7	--	26.6	--	0.28	--	35.58
218	--	--	--	--	8.7	--	26.5	--	0.45	--	35.65
219	--	--	--	--	8.6	--	26.5	--	0.71	--	35.80
220	--	--	--	--	8.5	--	26.1	--	0.87	--	35.70
221	--	--	--	--	8.5	--	26.2	--	0.93	--	35.63
222	--	--	--	--	8.6	--	26.4	--	1.11	--	36.11
223	--	--	--	--	8.6	--	26.3	--	1.40	--	36.3
224	--	--	--	--	8.5	--	25.9	--	2.60	--	37.0
225	--	--	--	--	8.1	--	24.8	--	6.84	--	39.74

TABLE 3
COMPOSITION OF FIBERS (continued)

TEST NO.	MISCELLANEOUS SO_3	Misc.	SUB TOTAL	TOTAL
Composition of Fibers with La_2O_3 additions				
--	--	--	--	99.63
213	--	--	--	99.68
214	--	--	--	99.28
215	--	--	--	98.54
Composition of Fibers with Cr_2O_3 additions				
216	--	--	--	99.72
Composition of Fibers with Na_2O additions				
17	--	--	--	100.34
218	--	--	--	100.21
219	--	--	--	100.26
220	--	--	--	100.40
221	--	--	--	99.99
222	--	--	--	100.37
223	--	--	--	100.36
224	--	--	--	100.06
225	--	--	--	100.1

TABLE 3

COMPOSITION OF FIBERS

TEST NO.	ACIDIC OXIDES B_2O_3	SiO_2	P_2O_5	SUB TOTAL	AMPHOTERIC OXIDES TiO_2	Al_2O_3	ZrO_2	SUB TOTAL
Composition of Conventional Mineral Wools								
226	-	40.0	-	40.0	0.37	9.1	0.03	9.50
	-	39.9	0.02	39.92	1.11	12.85	0.03	13.99
228	-	37.65	0.84	38.49	2.35	9.85	0.04	12.24
229	-	41.75	0.12	41.87	1.07	16.0	0.03	17.10
Composition of Refractory Fibers (Fibers with less than 25% Basic Oxides)								
231	-	31.0	-	31.0	-	47.5	0.02	47.52
232	-	37.1	-	37.1	-	59.2	-	59.2
233	-	50.0	-	50.0	-	40.0	-	40.0
234	-	54.0	-	54.0	-	46.0	-	46.0
235	-	58.47	1.15	59.62	0.98	24.54	0.03	25.55
236	-	52.1	-	52.1	1.76	44.4	.23	46.39
237	-	52.0	-	52.0	1.71	42.2	2.93	46.84
238	-	49.8	-	49.8	1.60	38.3	9.32	49.22
239	-	48.6	-	48.6	1.55	36.2	12.3	50.05
40	-	47.8	-	47.8	1.50	34.4	15.1	51.00
41	-	46.2	-	46.2	1.40	31.0	20.7	53.10
42	-	28	-	28	19	50	3	72
43	-	64.5	-	64.5	-	27.4	-	27.4

TABLE 3 (cont'd.)

COMPOSITION OF FIBERS

TEST	BASIC OXIDES												MISCELLANEOUS		
NO.	FeO_3	MnO	La_2O_3	Cr_2O_3	MgO	Li_2O	CaO	BaO	Na_2O	K_2O	SUB TOTAL	SO_3	Misc.	SUB TOTAL	TOTAL
Composition of Conventional Mineral Wools															
226	0.47	0.64	-	0.02	11.2	0.01	36.5	0.04	0.54	0.55	49.97	0.1	0.59	0.69	100.16
	0.35	0.24	-	0.00	6.05	0.01	38.55	0.12	0.23	0.27	45.82	0.67	0.07	0.74	100.47
228	9.7	0.22	-	0.04	12.95	0.01	23.55	0.07	2.01	0.80	49.35	0.42	0.19	0.61	100.69
229	3.75	0.23	-	0.02	6.45	0.63	27.75	0.03	2.04	0.63	41.53	0.56	0.08	0.64	101.14
Composition of Refractory Fibers (Fibers with less than 25% Basic Oxides															
231	-	-	-	-	-	-	1.2	-	20.2	-	21.4	-	-	-	99.92
232	-	-	-	-	-	-	0.2	-	3.1	-	3.3	-	-	-	99.6
233	-	-	-	-	-	-	5.6	-	4.4	-	10.0	-	-	-	100
234	-	-	-	-	-	-	-	-	-	-	-	-	-	-	100
235	3.70	0.02	-	0.00	1.44	0.02	5.78	0.54	1.55	1.18	14.23	0.47	0.24	0.71	100.11
236	.83	-	-	-	0.07	-	0.12	-	.05	.06	1.13	-	-	-	99.62
237	.77	-	-	-	0.07	-	0.12	-	.05	.06	1.07	-	-	-	99.91
238	.72	-	-	-	0.07	-	0.12	-	.05	.06	1.02	-	-	-	100.04
239	.70	-	-	-	0.07	-	0.12	-	.05	.06	1.00	-	-	-	99.65
240	.68	-	-	-	0.07	-	0.12	-	.05	.06	.98	-	-	-	99.78
241	.63	-	-	-	0.07	-	0.12	-	.05	.06	0.93	-	-	-	100.23
242	-	-	-	-	-	-	-	-	-	-	-	-	-	-	100
243	-	-	-	-	-	8.4	-	-	-	-	8.4	-	-	-	100.3

TABLE 4

TEST RESULTS ON FIBERS MADE WITH ALUMINA ADDITIONS

	COMPOSITION, WT%							5 Hour Saline	E-119 Fire Test	
	Acidic Oxides	Amphoteric Oxides		Basic Oxides			Total	Extraction	Thickness	2 Hour
NO.	SiO_2	Al_2O_3	Total	CaO	MgO	Total	Analytical	ppm. Si	Density	Test**
0 to 1 1/2% Amphoteric Oxides										
1	32	0.2	0.22	39	29	68.1	100.37	*	*	*
2	31.3	0.2	0.22	33.3	35.5	68.9	100.47	*	*	*
3	41.9	0.28	0.30	57.5	0.1	57.7	99.95	80	-	-
4	43.5	0.33	0.35	46.0	10.4	56.5	100.40	58	-	-
5	43.7	0.25	0.27	39.8	16.6	56.5	100.52	46	2.0/1.27	F
6	45.0	0.50	0.52	54.4	0.1	54.6	100.17	75	-	-
7	46.5	0.20	0.22	9.2	45.1	54.4	101.17	*	*	*
8	48.2	0.20	0.22	5.0	47.6	52.7	101.17	*	*	*
9	47.9	0.22	0.24	19.3	33.5	52.9	101.09	50	-	-
10	48.5	0.56	0.58	8.8	43.0	51.9	101.03	51	-	-
11	48.6	0.56	0.58	13.3	38.3	51.7	100.93	46	-	-
12	49.2	0.42	0.44	28.0	22.9	51.0	100.69	67	-	-
13	49.2	0.17	0.19	3.4	48.3	51.8	101.24	*	*	*
14	50.0	0.10	0.12	7.0	43.0	50.1	100.27	56	-	-
15	50.7	0.10	0.12	15.7	33.7	49.5	100.37	60	-	-
16	51.1	0.45	0.47	29.8	19.0	48.9	100.52	65	-	-
17	51.2	0.33	0.35	39.7	9.0	48.8	100.40	51	2.0/2.59	F
18	53.2	0.64	0.66	2.8	44.3	47.2	101.11	56	-	F
19	53.4	0.28	0.30	45.6	0.1	45.8	99.55	77	2.0/1.97	F

* = Not Fiberizable

** P = Pass, F = Failed

EXPERIMENTAL DATA

	COMPOSITION, WT%							5 Hour Saline	E-119 Fire Test	
	Acidic Oxides	Amphoteric Oxides		Basic Oxides			Total	Extraction	Thickness	2 Hour
NO.	SiO_2	Al_2O_3	Total	CaO	MgO	Total	Analytical	ppm. Si	Density	Test**
0 to 1 1/2% Amphoteric Oxides										
20	53.8	0.33	0.35	35.1	10.8	46.0	100.20	83	2.0/1.97	F
21	53.9	0.40	0.42	25.5	20.5	46.1	100.47	68	–	–
22	54.5	1.00	1.02	7.5	36.5	44.1	99.67	30	–	–
23	55.9	0.08	0.10	43.0	0.45	43.55	99.60	51	2.0/1.94	F
24	56.0	0.40	0.42	27.0	17.0	44.1	100.57	69	2.0/2.12	F
25	56.35	0.20	0.24	34.4	8.25	42.75	99.39	70	2.0/1.87	F
26	56.4	0.91	0.93	35.1	7.39	42.59	99.97	47	–	–
27	57.0	1.03	1.05	24.5	17.6	42.2	100.30	46	–	–
28	57.0	1.09	1.11	35.0	6.84	41.94	100.10	40	–	–
29	57.25	0.92	0.94	36.95	3.95	41.1	99.56	56	1.88/2.20	F
10	57.8	0.75	0.78	34.75	6.2	41.05	99.85	–	2.0 /1.97	F
11	58.1	0.03	0.05	36.7	4.53	41.33	99.53	59	2.0 /1.91	F
12	58.2	1.08	1.10	35.7	4.79	40.59	99.94	80	2.0 /1.91	F
13	58.3	0.03	0.05	40.8	0.31	41.21	99.61	49	2.0 /1.91	F
4	58.4	0.37	0.39	15.3	26.3	41.7	100.54	61	2.0 /1.91	F
5	58.6	0.09	0.11	35.0	5.36	40.46	99.22	74	2.0 /1.94	P
6	58.7	0.05	0.07	40.2	0.27	40.57	99.39	58	2.0 /1.91	F
7	58.5	0.49	0.53	34.4	5.6	40.1	99.32	59	2.0 /2.01	P
8	58.8	0.41	0.43	35.4	6.2	41.7	100.98	56	–	–

= Not Fiberizable

** P = Poor, F = Failed

EXPERIMENTAL DATA

	COMPOSITION, WT%							5 Hour Saline	E-119 Fire Test	
	Acidic Oxides	Amphoteric Oxides		Basic Oxides			Total	Extraction	Thickness	2 Hour
NO.	SiO_2	Al_2O_3	Total	CaO	MgO	Total	Analytical	ppm. Si	Density	Test**
0 to 1 1/2% Amphoteric Oxides										
39	58.9	0.08	0.10	34.2	6.10	40.4	99.45	67	2.0/1.86	P
40	59.0	0.24	0.26	35.9	3.8	39.9	99.21	49	2.0/1.97	P
41	59.1	0.09	0.11	40.3	0.43	40.83	100.09	68	2.0/1.90	P
42	59.2	0.24	0.26	4.7	36.8	41.60	101.11	47	2.5/1.4	F
43	59.15	0.32	0.34	35.55	4.75	40.40	99.94	60	2.0/1.95	P
44	59.4	0.04	0.06	29.8	10.7	40.60	100.11	61	2.0/1.92	P
45	59.5	0.02	0.04	34.2	5.98	40.28	99.87	77	2.0/1.90	P
46	59.5	0.02	0.04	32.1	8.16	40.36	99.95	73	2.0/1.89	F
47	59.6	1.43	1.45	22.5	16.8	39.6	100.8	51	2.0/1.88	F
48	59.6	0.03	0.05	28.7	11.4	40.2	99.9	70	2.0/1.91	P
50	59.8	0.28	0.30	40.5	0.11	40.71	100.86	30	2.0/2.01	P
51	59.9	1.48	1.50	25.8	12.9	39.0	100.55	47	2.0/1.98	P
52	59.9	1.31	1.33	28.1	11.0	39.4	100.78	45	2.0/1.95	P
53	60.0	1.41	1.43	22.3	16.4	39.0	100.58	41	2.0/1.91	P
54	60.3	0.17	0.19	32.3	6.36	38.76	99.30	59	2.0/1.89	P
55	60.4	1.05	1.07	28.5	9.85	38.45	99.97	45	2.0/1.95	P
56	60.5	1.11	1.13	27.9	10.7	38.9	100.68	36	2.0/1.94	F
57	60.7	0.93	0.95	28.7	9.47	38.27	99.97	51	2.0/1.93	P
58	60.8	0.2	0.22	36.	3.	39.10	100.17	56	—	—

: = Not Fiberizable

** P = Poor, F = Failed

EXPERIMENTAL DATA

	COMPOSITION, WT%							5 Hour Saline	E-119 Fire Test	
	Acidic Oxides	Amphoteric Oxides		Basic Oxides			Total	Extraction	Thickness	2 Hour
NO.	SiO_2	Al_2O_3	Total	CaO	MgO	Total	Analytical	ppm. Si	Density	Test**
0 to 1 1/2% Amphoteric Oxides										
59	61.7	0.02	0.04	32.6	5.19	37.89	99.68	65	2.0/1.97	P
60	62.4	0.04	0.06	21.7	15.5	37.3	99.81	76	2.0/1.88	P
61	62.5	0.02	0.04	30.3	6.64	37.04	99.63	66	2.0/1.92	P
62	62.5	0.03	0.05	29.5	7.70	37.30	99.90	64	2.0/1.82	P
63	63.1	0.02	0.04	31.1	5.28	36.48	99.67	46	2.0/1.95	P
64	63.1	1.25	1.27	25.2	10.2	35.5	99.92	19	2.0/1.96	P
65	63.5	1.49	1.51	24.0	10.9	35.0	100.06	12	2.0/1.91	P
66	63.8	1.13	1.15	28.4	5.79	34.29	99.29	52	2.0/2.01	P
67	63.8	1.41	1.43	22.8	11.8	34.7	99.98	17	2.0/1.88	P
68	64.1	1.23	1.25	30.97	2.60	33.67	99.07	7	2.0/1.88	P
69	64.1	1.47	1.49	28.6	4.83	33.53	99.17	49	2.0/1.99	P
70	65.3	0.03	0.05	27.4	6.68	34.18	99.58	37	2.0/1.91	P
71	65.4	1.15	1.17	3.12	30.1	33.32	99.94	46	2.0/1.88	F
72	65.6	0.01	0.03	27.4	6.50	34.0	99.68	35	2.0/2.00	P
73	65.8	0.02	0.04	28.6	5.21	33.91	99.80	44	—	—
74	65.9	0.03	0.05	21.9	11.8	33.8	99.80	30	2.0/1.87	P
75	65.9	0.03	0.05	25.8	7.88	33.78	99.78	25	2.0/1.91	P
76	65.4	1.15	1.17	3.12	30.1	33.23	99.84	46	2.0/1.88	F

= Not Fiberizable

** P = Poor, F = Failed

EXPERIMENTAL DATA

NO.	COMPOSITION, WT% Acidic Oxides SiO_2	Amphoteric Oxides Al_2O_3	Amphoteric Oxides Total	Basic Oxides CaO	Basic Oxides MgO	Basic Oxides Total	Total Analytical	5 Hour Saline Extraction ppm. Si	E-119 Fire Test Thickness Density	E-119 Fire Test 2 Hour Test**
0 to 1 1/2% Amphoteric Oxides (Cont.)										
77	66.1	0.59	0.61	4.02	28.7	33.02	99.88	50	–	F
78	67.1	–	–	6.43	26.5	33.03	100.18	78	2.0/1.89	F
79	67.2	0.02	0.04	8.67	24.0	32.77	100.06	84	2.0/2.03	F
80	68.4	–	–	1.6	30.1	31.8	100.25	*	*	*
81	68.6	0.25	0.27	29.0	1.09	30.19	99.11	18	2.0/2.00	P
82	68.8	–	–	10.2	21.3	31.6	100.45	31	–	–
83	68.9	0.03	0.05	18.1	12.7	30.9	99.9	30	2.0/2.00	P
84	69.0			7.2	23.8	31.0	100.05	18	–	–
1 1/2% to 3% Amphoteric Oxides										
85	50.0	2.00	2.02	5.0	43.0	48.1	100.17	–	*	*
86	52.6	2.00	2.02	3.8	41.7	45.6	100.27	51	2.0/1.88	F
87	56.1	2.41	2.43	30.3	10.6	41.0	99.58	39	2.0/1.89	F
88	56.2	1.82	1.84	24.4	17.3	41.8	99.89	65	–	–
89	58.1	2.01	2.03	3.83	36.3	40.43	100.71	44	2.0/1.99	P
90	58.9	2.26	2.28	36.6	1.4	38.1	99.33	18	2.0/1.82	P
91	59.0	2.93	2.95	36.3	1.0	37.4	99.40	9	2.0/1.87	P
92	59.4	0.38	2.69	34.9	2.1	37.1	99.24	25	2.0/2.06	P
93	59.8	2.54	2.56	27.4	10.0	37.5	99.91	11	–	–
94	60.1	1.68	1.70	28.0	9.9	38.0	99.85	29	2.0/1.98	P

* = Not Fiberizable

* P = Pass, F = Failed

EXPERIMENTAL DATA

	COMPOSITION, WT%							5 Hour Saline	E-119 Fire Test	
	Acidic Oxides	Amphoteric Oxides		Basic Oxides			Total	Extraction	Thickness	2 Hour
NO.	SiO_2	Al_2O_3	Total	CaO	MgO	Total	Analytical	ppm. Si	Density	Test**
1 1/2% to 3% Amphoteric Oxides (Cont.)										
95	60.2	2.21	2.23	32.7	4.9	37.7	100.18	50	2.0/2.04	P
96	61.4	2.17	2.19	26.2	10.1	36.4	100.04	18	2.0/1.87	P
97	61.4	1.66	1.68	29.9	6.9	36.9	100.03	61	2.0/1.91	P
98	61.8	2.84	2.86	34.0	0.2	34.3	99.01	51	2.0/1.93	P
99	62.0	2.81	2.83	34.1	0.2	34.4	99.28	55	2.0/1.90	P
100	62.1	2.75	2.77	33.8	0.2	34.1	99.02	13	2.0/1.91	P
101	62.7	1.79	1.81	25.6	9.4	35.1	99.66	18	2.0/1.96	P
102	63.0	2.54	2.56	33.1	0.2	33.4	99.05	37	2.0/1.87	P
103	63.9	1.84	1.86	30.7	2.5	33.3	99.11	38	2.0/1.94	P
104	64.1	1.83	1.85	17.7	16.3	34.3	100.4	12	2.0/1.95	P
105	65.1	2.15	2.17	9.74	23.1	33.15	100.57	17	-	P
106	65.6	1.56	1.58	2.7	29.7	32.5	99.73	33	2.0/1.91	P
107	66.7	1.80	1.82	30.7	0.1	30.9	99.47	2	2.0/1.90	P
3 to 4% Amphoteric Oxides										
108	49.8	3.5	3.52	4.98	40.9	46.18	99.65	33	-	-
109	50.3	3.58	3.60	45.0	0.64	45.74	99.69	19	2.0/1.96	F
110	55.1	3.77	3.79	7.89	33.7	41.89	100.93	33	2.0/2.06	P

* = Not Fiberizable ** P = Pass, F = Failed

EXPERIMENTAL DATA

	COMPOSITION, WT%							5 Hour Saline	E-119 Fire Test	
	Acidic Oxides	Amphoteric Oxides		Basic Oxides			Total	Extraction	Thickness	2 Hour
NO.	SiO_2	Al_2O_3	Total	CaO	MgO	Total	Analytical	ppm. Si	Density	Test**
3% to 4% Amphoteric Oxides (Cont.)										
111	55.6	0.24	3.66	37.1	4.65	41.85	101.16	-	2.0/2.12	F
112	56.5	0.35	3.65	36.51	4.17	40.78	100.98	-	2.0/1.99	F
113	56.7	3.52	3.54	23.5	16.2	39.8	100.09	19	2.0/1.89	F
114	56.7	3.06	3.08	23.4	16.6	40.28	100.11	40	2.0/4.02	F
115	56.88	0.32	3.64	36.45	4.00	40.45	101.02	51	-	-
115a	57.5	3.29	3.31	37.7	0.75	38.55	99.41	6	2.0/1.93	F
116	58.1	3.05	3.07	25.6	12.8	38.5	99.72	20	2.0/1.9	F
117	58.2	3.75	3.77	36.4	0.67	37.17	99.19	38	2.0/2.0	F
119	58.80	3.76	3.78	36.7	0.24	37.04	99.67	28	2.0/1.97	F
120	61.2	3.77	3.79	34.0	0.24	34.34	99.38	18	2.0/1.94	P
4 to 6% Amphoteric Oxides										
121	49.7	4.04	4.06	26.4	19.6	46.1	99.91	37	-	-
122	55.8	5.20	5.22	30.1	9.2	39.4	100.47	7	2.0/1.88	F
123	56.85	5.40	5.41	31.8	5.65	37.55	99.91	4	2.0/1.99	F
124	57.0	4.68	4.70	22.0	15.6	37.7	99.45	32	2.0/2.00	F

* = Not Fiberizable

** P = Pass, F = Failed

EXPERIMENTAL DATA

	COMPOSITION, WT%							5 Hour Saline	E-119 Fire Test	
	Acidic Oxides	Amphoteric Oxides		Basic Oxides			Total	Extraction	Thickness	2 Hour
NO.	SiO_2	Al_2O_3	Total	CaO	MgO	Total	Analytical	ppm. Si	Density	Test**
6 to 8% Amphoteric Oxides										
125	39.2	6.90	6.92	38.5	14.0	52.6	98.72	37	-	-
126	46.9	7.66	7.68	44.8	0.3	45.2	99.83	6	2.0/1.97	F
127	49.3	6.40	6.42	25.3	18.4	43.8	99.57	19	2.0/2.0	F
128	50.4	7.45	7.48	26.2	15.2	41.5	99.43	18	2.0/3.17	F
129	54.7	7.60	7.62	30.7	6.5	37.3	99.67	7	2.0/1.98	F
130	56.1	6.34	6.36	30.6	6.9	37.6	100.11	4	2.0/2.04	F
131	57.9	6.7	6.72	5.9	29.7	35.6	100.27	2	-	-
132	58.5	6.16	6.18	31.2	4.0	35.2	99.93	2	2.0/2.01	F
133	59.7	7.08	7.10	27.9	5.1	33.1	99.9	2	2.0/2.04	F
8 to 10% Amphoteric Oxides										
134	38.6	9.3	9.32	38.4	13.7	52.2	100.17	12	-	-
135	42.8	8.8	9.13	36.7	9.6	46.76	98.69	13	-	-
136	44.5	8.76	8.78	45.5	0.52	46.12	99.45	3	-	-
137	52.1	8.9	8.92	23.7	16.2	40.0	101.02	1.2	-	-
138	52.5	9.67	9.69	33.5	4.21	37.81	100.05	1.0	2.0/1.99	F
139	53.7	8.7	8.72	22.5	16.3	38.9	101.37	1.7	-	-
140	56.6	9.2	9.22	23.5	10.9	34.5	100.37	1.2	2.0/2.05	F

* = Not Fiberizable

** P = Pass, F = Failed

EXPERIMENTAL DATA

	COMPOSITION, WT%							5 Hour Saline Extraction	E-119 Fire Test	
	Acidic Oxides	Amphoteric Oxides		Basic Oxides			Total		Thickness	2 Hour
NO.	SiO_2	Al_2O_3	Total	CaO	MgO	Total	Analytical	ppm. Si	Density	Test**
10 to 12% Amphoteric Oxides										
141	41.0	10.05	10.07	48.25	0.3	48.70	99.87	6	2.0/2.00	F
142	51.3	10.9	10.92	37.2	0.2	37.5	99.77	0.8	2.0/2.04	F
143	52.4	10.7	10.72	23.1	16.1	39.3	102.42	0.7	2.0/2.00	F
144	52.7	10.2	10.22	22.1	16.0	38.2	101.12	0.5	-	-
12 to 20% Amphoteric Oxides										
145	41.5	13.0	13.02	44.2	0.5	44.8	99.37	1.2	-	-
146	49.8	18.0	18.02	31.5	0.2	32.02	99.89	0.5	-	-
147	55.6	12.9	12.92	13.2	18.4	31.7	100.27	1.8	2.0/2.54	F
20 to 30% Amphoteric Oxides										
148	36.5	28.4	28.42	34.4	0.3	34.8	99.77	0.6	-	-
149	40.3	21.5	21.52	37.5	0.3	37.9	99.77	0.8	-	-
150	42.6	25.7	25.72	31.2	0.3	31.6	99.97	0.6	-	-
151	48.4	22.4	22.42	16.5	12.6	29.2	100.07	0.5	2.0/2.01	F
152	59.9	22.8	22.82	3.1	14.0	17.2	99.97	0.7	2.0/2.01	F
30 to 40% Amphoteric Oxides										
153	45.9	31.3	31.32	5.9	16.7	22.7	99.97	2.3	-	-

* = Not Fiberizable ** P = Pass, F = Failed

TABLE 5

FIBERS MADE WITH VARIOUS ADDITIVE CONSTITUENTS

	ANALYSES							5 Hour Saline	E-119 Fire Test	
NO.	Acidic Oxides	Amphoteric Oxides	Basic Oxides	Misc.	Total	% Additive (Incl.Total)		Extraction ppm. Si	Thickness Density	2 Hour Test
Fibers with B_2O_3 Additions										
164	65.12	0.06	35.3	-	100.48	0.32%	B_2O_3	53	2.0/1.94	P
165	64.42	1.20	34.8	-	100.42	0.52%	"	20	2.0/1.88	P
166	65.24	0.06	35.2	-	100.5	0.64%	"	43	2.0/1.89	P
167	65.32	0.06	35.2	-	100.58	0.82%	"	45	2.0/2.00	P
168	65.43	0.06	34.9	-	100.39	1.33%	"	47	2.0/1.95	P
169	65.47	0.06	34.9	-	100.43	1.37%	"	45	2.0/ -	P
170	65.82	0.06	34.6	-	100.48	2.22%	"	46	2.0/2.02	P
171	68.01	0.06	32.0	-	100.07	8.41%	"	52	2.0/6.45	P
Fibers with P_2O_5 addition										
172	55.65	0.48	43.58	0.02	99.7	6.06%	P_2O_5	71	2.0/1.94	F
Fibers with TiO_2 addition										
173	48.6	51.4	-	-	100.	10%	TiO_2	0.4	2.01/1.94	P

NO.	ANALYSES: Acidic Oxides	Amphoteric Oxides	Basic Oxides	Misc.	Total	% Additive (Incl.Total)	5 Hour Saline Extraction ppm. Si	E-119 Fire Test: Thickness Density	E-119 Fire Test: 2 Hour Test
Fibers with ZrO_2 additions									
174	63.5	1.10	35.92	-	100.52	0.21% ZrO_2	25	2.0/2.01	P
175	59.2	0.73	39.51	-	99.44	0.40% "	48	2.0/2.00	P
176	59.5	0.73	39.52	-	99.75	0.42% "	55	-	-
177	59.7	0.84	39.16	-	99.70	0.50% "	32	-	-
178	60.0	0.90	38.78	-	99.68	0.54% "	40	-	-
179	59.2	0.93	37.98	-	98.11	0.58% "	46	2.0/2.02	P
180	54.3	1.88	43.12	.01	99.31	0.58% "	67	2.0/2.00	F
181	59.2	1.15	37.73	-	98.08	0.83% "	57	2.0/2.03	P
182	46.85	2.89	49.98	.02	99.74	0.84% "	44	2.0/2.17	F
182a	59.4	2.69	36.96	.02	99.05	2.31% "	25	2.0/2.00	P
183	59.05	2.95	38.07	-	100.09	2.65% "	38	2.0/2.20	P
184	57.96	3.53	38.72	-	100.21	3.11% "	25	2.0/2.37	F
185	57.80	3.68	38.14	-	99.62	3.12% "	10	2.0/2.03	F
186	59.05	3.65	39.51	-	102.21	3.27% "	15	2.1/2.11	P
187	56.88	3.62	40.45	-	100.95	3.30% "	51	-	-
188	57.7	3.50	39.0	-	100.20	3.30% "	13	2.0/2.06	P
189	58.19	3.75	38.65	-	100.59	3.36% "	12	-	-
190	57.86	3.73	38.88	-	100.47	3.37% "	-	2.0/2.00	F
191	58.6	4.25	36.22	-	99.07	3.67% "	7	2.0/2.00	P
192	58.4	4.34	35.79	-	98.53	3.69% "	3	2.0/2.00	P
193	58.65	7.87	35.36	.01	99.89	4.50% "	1.3	2.0/2.07	F

Test No.	ANALYSES Acidic Oxides	Amphoteric Oxides	Basic Oxides	Misc.	Total	% Additive (Incl.Total)	5 Hour Saline Extraction ppm. Si	E-119 Fire Test Thickness Density	2 Hour Test
Fibers with FeO_3 additions									
194	64.9	0.06	35.38	-	100.34	0.06% FeO_3 & MnO	56	2.01/1.88	P
195	49.8	18.02	31.92	0.07	99.81	0.22% " "	0.5	-	-
196	50.4	7.49	42.04	0.07	100.00	0.52% " "	18	-	-
197	64.34	0.06	34.7	-	99.1	0.50% " "	51	2.0/1.91	P
198	63.70	1.20	33.02	-	98.62	0.69% " "	24	2.0/1.88	F
199	63.54	1.20	33.46	-	98.20	0.72% " "	35	2.0/2.00	P
200	38.9	6.72	54.40	0.07	100.09	0.80% " "	17	-	-
201	64.3	0.06	35.96	-	100.32	0.96% " "	45	2.0/1.88	P
202	44.6	0.94	51.92	-	97.46	1.02% " "	49	-	-
203	63.3	1.15	34.99	-	99.44	1.61% " "	12	2.0/1.95	F
204	63.6	0.06	36.62	-	100.15	1.92% " "	31	2.0/1.91	P
205	43.8	15.28	40.94	0.13	100.02	2.94% " "	1.3	-	-
206	62.3	1.20	36.05	-	99.55	3.05% " "	7	2.0/1.98	F
207	63.3	0.06	36.95	-	100.31	3.45% " "	18	2.0/1.88	F
208	43.9	14.32	41.6	-	99.82	3.50% " "	2	-	-
209	62.0	0.06	38.31	-	100.37	4.81% " "	13	2.0/1.98	F
210	60.0	2.0	38.0	-	100.0	8.0% " "	0.9	2.0/2.00	F
211	60.0	-	40.0	-	100.0	20.0% " "	0.7	2.0/2.00	F

Test No.	ANALYSES Acidic Oxides	Amphoteric Oxides	Basic Oxides	Misc.	Total	% Additive (Incl.Total)	5 Hour Saline Extraction ppm. Si	E-119 Fire Test Thickness Density	2 Hour Test
Fibers with La_2O_3 additions									
212	58.1	0.06	41.47	-	99.63	0.00% La_2O_3	76	2.0/1.97	F
213	57.8	0.06	41.82	-	99.68	0.56% "	69	2.0/1.97	F
214	57.5	0.06	41.72	-	99.28	0.72% "	78	2.0/1.98	F
215	56.9	0.06	41.58	-	99.54	0.92% "	70	2.0/1.98	F
Fibers with Cr_2O_3 additions									
216	62.6	0.51	36.61	-	99.72	0.09% Cr_2O_3	28	2.0/2.16	P
Fibers with Na_2O additions									
217	64.7	0.06	35.58	-	100.34	0.28% Na_2O	45	2.0/1.91	P
218	64.5	0.06	35.68	-	100.21	0.45% "	57	2.0/1.97	P
219	64.4	0.06	35.80	-	100.26	0.71% "	54	2.0/1.97	P
220	63.5	1.20	35.70	-	100.40	0.87% "	30	2.0/1.90	P
221	64.3	0.06	35.63	-	99.99	0.93% "	51	2.0/1.90	P
222	64.2	0.06	36.11	-	100.37	1.11% "	57	2.0/1.99	P
223	64.0	0.06	36.3	-	100.36	1.40% "	43	2.0/1.99	P
224	63.0	0.06	37.0	-	100.06	2.60% "	50	2.0/2.16	F
225	60.3	0.06	39.74	-	100.1	6.84% "	70	2.0/1.87	F

Test No.	ANALYSES Acidic Oxides	Amphoteric Oxides	Basic Oxides	Misc.	Total	% Additive (Incl.Total)	5 Hour Saline Extraction ppm. Si	E-119 Fire Test Thickness Density	2 Hour Test
Conventional Mineral Wool Fibers									
226	40.0	9.50	49.97	0.69	100.16	-	7	2.0/3.50	F
227	39.92	13.99	45.82	0.74	100.47	-	1.2	2.0/5.23	F
228	38.49	12.24	49.35	0.61	100.69	-	0.6	2.0/3.42	F
229	41.87	17.10	41.53	0.64	101.14	-	1.0	2.0/3.86	F
Refractory Fibers - (Fibers with less than 25% Basic Oxides)									
231	31.0	47.52	21.4	-	99.92	-	2	2.0/2.10	F
232	37.1	59.2	3.3	-	99.6	-	0.6	2.0/5.38	F
233	50.0	40.0	10.0	-	100	-	0.8	2.0/2.00	P
234	54.0	46.0	-	-	100	-	0.3	2.0/2.00	P
235	59.62	25.55	14.23	0.7	100.11	-	0.3	2.0/2.00	P
236	52.1	46.39	1.13	-	99.62	-	1.0	-	-
237	52.0	46.84	1.07	-	99.91	-	0.4	-	-
238	49.8	49.22	1.02	-	100.04	-	0.3	-	-
239	48.6	50.05	1.00	-	99.65	-	0.4	-	-
240	47.8	51.00	0.98	-	99.78	-	0.3	-	-
241	46.2	53.10	0.93	-	100.23	-	0.4	-	-
242	28	72	-	-	100	-	0.5	-	-
243	64.5	27.4	8.4	-	100.3	-	0.8	2.0/1.85	F

TABLE 6

CONTINUOUS SERVICE TEMPERATURE
FOR CONSTANT SiO_2/CaO/MgO RATIOS

SiO_2/CaO/MgO Ratio	0	5	10	20	30
	Continuous Service Temperature for max 5% shrinkage °F				
50/50/0	1480	1480	1470	1420	1550
50/40/10	1440	1430	1420	1400	1520
50/30/10	1400	1380	1370	1350	1480
60/40/0	1500	1460	1460	1460	1600
60/30/10	1430	1420	1400	1410	1520
60/20/20	1380	1370	1360	1350	1500

Reasonable modifications and variations are possible from the foregoing disclosure without departing from either the spirit or scope of the invention as defined in the claims.

CLAIMS

1. A process for decomposing a silica-containing fiber comprising the steps of:

1. providing an inorganic fiber prepared from a composition consisting essentially of:

(a) 0.06-10 wt% of a material selected from the group consisting of Al_2O_3, ZrO_2, TiO_2, B_2O_3, iron oxides and mixtures thereof;

(b) 35-70 wt% SiO_2;

(c) 0-50 wt% MgO; and

(d) the remainder consisting essentially of CaO, the total being 100% by weight;

2. subjecting the silica-containing fiber to a physiological saline fluid; and

3. extracting the silica at a rate of at least 5 parts per million (ppm) of silicon in 5 hours, thereby decomposing the silica-containing fiber.

2. The process of Claim 1 wherein the composition of subsection 1(a) ranges from 0.06-5 wt% of material selected from the group consisting of Al_2O_3, ZrO_2, TiO_2, B_2O_3, iron oxides and mixtures thereof.

3. The process of Claim 1 wherein the composition of subsection 1(c) ranges from 0.25-50 wt% MgO.

4. The process of Claim 1 wherein the composition consists essentially of:

(a) 0.06-1.5 wt% of Al_2O_3, ZrO_2, TiO_2, B_2O_3, iron oxides and mixtures thereof;

(b) 40-70 wt% SiO_2;

(c) 0-50 wt% MgO; and

(d) the remainder consisting essentially of CaO, the total being 100% by weight.

5. The process of Claim 4 wherein the composition in subsection 1(c) ranges from 0.25-50 wt% MgO.

6. The process of Claim 1 wherein the composition consists essentially of:

(a) 1.5-3 wt% of Al_2O_3, ZrO_2, TiO_2, B_2O_3, iron oxides and mixtures thereof;

(b) 40-66 wt% SiO_2;

(c) 0-50 wt% MgO; and

(d) the remainder consisting essentially of CaO, the total being 100% by weight.

7. The process of Claim 1 wherein the composition of subsection 1(c) ranges from 0.25-50 wt% MgO.

8. The process of Claim 1 wherein the composition consists essentially of:

(a) 3-4 wt% of Al_2O_3, ZrO_2, TiO_2, B_2O_3, iron oxides and mixtures thereof;

(b) 40-63 wt% SiO_2;

(c) 0-50 wt% MgO; and

(d) the remainder consisting essentially of CaO, the total being 100% by weight.

9. The process of Claim 8 wherein the composition of subsection 1(c) ranges from 0.25-50 wt% MgO.

10. The process of Claim 1 wherein the composition consists essentially of:

(a) 4-6 wt% of Al_2O_3, ZrO_2, TiO_2, B_2O_3, iron oxides and mixtures thereof;

(b) 40-60 wt% SiO_2;

(c) 0-25 wt% MgO; and

(d) the remainder consisting essentially of CaO, the total being 100% by weight.

11. The process of Claim 10 wherein the composition of subsection 1(c) ranges from 0.25-25 wt% MgO.

12. The process of Claim 1 wherein the composition consists essentially of:

(a) 6-8 wt% of Al_2O_3, ZrO_2, TiO_2, B_2O_3, iron oxides and mixtures thereof;

(b) 35-54 wt% SiO_2;

(c) 0-25 wt% MgO; and

(d) the remainder consisting essentially of CaO, the total being 100% by weight.

13. The process of Claim 12 wherein the composition of subsection 1(c) ranges from 0.25-25 wt% MgO.

14. The process of Claim 1 wherein the composition consists essentially of:

(a) 8-10 wt% of Al_2O_3, ZrO_2, TiO_2, B_2O_3, iron oxides and mixtures thereof;

(b) 35-54 wt% SiO_2;

(c) 0-20 wt% MgO; and

(d) the remainder consisting essentially of CaO, the total being 100% by weight.

15. The process of Claim 14 wherein the composition of subsection 1(c) ranges from 0.25-20 wt% MgO.

16. The process of Claim 1 wherein the fiber has a diameter of less than 3.5 microns.

17. The process of Claim 1 wherein the silicon extraction rate is at least 20 ppm, the Al_2O_3 content is about 0.06-7 wt%, and the SiO_2 content is about 40-66 wt%.

18. The process of Claim 1 wherein the silicon extraction rate is at least about 50 ppm, the Al_2O_3 content is about 0.06-3 wt%, and the SiO_2 content is about 40-60 wt%.

19. The process of Claim 1 wherein the silicon extraction rate is at least about 50 ppm, the Al_2O_3 content is about 0.06-0.75 wt%, and the SiO_2 content is about 40-60 wt%.

20. A process of protecting a structural wall from fire comprising the steps of:

1. providing a fiber blanket having a bulk density in the range of about 1.5 to about 3 lbs. per cubic foot (pcf); wherein the fiber blanket has the ability to pass ASTM E-119 two-hour fire test; the fibers in the blanket have a diameter less than about 3.5 microns; and the fiber is an inorganic fiber prepared from a composition consisting essentially of:

(a) 0-7 wt% of Al_2O_3, ZrO_2, TiO_2, B_2O_3, iron oxides and mixtures thereof;

(b) 58-70 wt% SiO_2

(c) 0-21 wt% MgO;

(d) 0-2 wt% alkali metal oxide; and

(e) the remainder consisting essentially of CaO, the total being 100% by weight; and

2. placing the blanket next to the wall, and thereby protecting the wall from fire.

21. The process of Claim 20 wherein the composition of subsection 1(a) ranges from 0.06-7 wt% of Al_2O_3, ZrO_2, TiO_2, B_2O_3, iron oxides and mixtures thereof.

22. The process of Claim 20 wherein the composition of subsection 1(c) ranges from 0.25-21 wt% MgO.

23. The process of Claim 20 wherein the composition consists essentially of:

(a) 0.06-3.0 wt% of Al_2O_3, ZrO_2, TiO_2, B_2O_3, iron oxides and mixtures thereof;

(b) 58.5-70 wt% SiO_2;

(c) 0-21 wt% MgO;

(d) 0-2 wt% alkali metal oxide; and

(e) the remainder consisting essentially of Cao, the total being 100% by weight.

24. The process of Claim 20 wherein the composition of subsection 1(c) ranges from 0.25-21 wt% MgO.

25. The process of Claim 20 wherein the composition consists essentially of:

(a) from about 3 wt% up to and including 4 wt% of Al_2O_3, ZrO_2, TiO_2, B_2O_3, iron oxides and mixtures thereof;

(b) 58-63 wt% SiO_2;

(c) 0-8 wt% MgO;

(d) 0-2 wt% alkali metal oxide; and

(e) the remainder consisting essentially of CaO, the total being 100% by weight.

26. The process of Claim 25 wherein the composition in subsection 1(c) ranges from 0.25-8 wt% MgO.

27. The process of Claim 25 wherein the composition consists essentially of:

(a) from about 4 wt% up to and including 6 wt% of Al_2O_3, ZrO_2, TiO_2, B_2O_3, iron oxides and mixtures thereof;

(b) 58-61 wt% SiO_2;

(c) 0-7 wt% MgO;

(d) 0-2 wt% alkali metal oxide; and

(e) the remainder consisting essentially of Cao, the total being 100% by weight.

28. The process of Claim 25 wherein the composition of subsection 1(c) ranges from 0.25-7 wt% MgO.

29. An inorganic fiber having an average fiber diameter of less than about 3.5 microns, a silicon extraction rate greater than about 0.02 wt% Si/day in a physiological saline solution and having a composition consisting essentially of about:

(a) 0.06-5.0 wt% of material selected from the group consisting of Al_2O_3, ZrO_2, TiO_2, B_2O_3, iron oxides and mixtures thereof;

(b) 35-70 wt% SiO_2;

(c) 0-50 wt% MgO; and

(d) the remainder consisting essentially of Cao, the total being 100 wt%.

30. An inorganic fiber having a silicon extraction of at least about 10 ppm over a 5 hour period in physiological saline solution and having a composition consisting essentially of about:

(a) 0.06-1.5 wt% of material selected from the group consisting of Al_2O_3, ZrO_2, TiO_2, B_2O_3, iron oxides and mixtures thereof;

(b) 40-70 wt% SiO_2;

(c) 0-50 wt% MgO; and

(d) the remainder consisting essentially of CaO, the total being 100 wt%.

31. An inorganic fiber according to Claim 30 having a silicon extraction of at least about 20 ppm, an average fiber diameter of less than about 3.5 microns, and having an SiO_2 content of about 40-66 wt%.

32. An inorganic fiber according to Claim 30 having a silicon extraction of at least about 50 ppm and having an SiO_2 content of about 40-60 wt% and a MgO content of about 0.25-25 wt%.

33. An inorganic fiber having a silicon extraction of at least about 10 ppm over a 5 hour period in physiological saline solutions and having a composition consisting essentially of about:

(a) 1.5-3 wt% of material selected from the group consisting of Al_2O_3, ZrO_2, TiO_2, B_2O_3, iron oxides and mixtures thereof;

(b) 40-66 wt% SiO_2;

(c) 0-50 wt% MgO; and

(d) the remainder consisting essentially of CaO, the total being 100 wt%.

34. An inorganic fiber according to Claim 33 having a silicon extraction of at least about 20 ppm, an average fiber diameter of less than about 3.5 microns, and an MgO content of from about .25-50 wt%.

35. An inorganic fiber according to Claim 33 having a silicon extraction of at least about 50 ppm, an SiO_2 content of from about 40-54 wt%, and an MgO content of from about 0.25-18 wt%.

36. An inorganic fiber having a silicon extraction of at least about 10 ppm over a 5 hour period

in physiological saline solutions and having a composition consisting essentially of about:

(a) 3-4 wt% of material selected from the group consisting of Al_2O_3, ZrO_2, TiO_2, B_2O_3, iron oxides and mixtures thereof;

(b) 40-63 wt% SiO_2;

(c) 0-50 wt% MgO; and

(d) the remainder consisting essentially of CaO, the total being 100 wt%.

37. An inorganic fiber according to Claim 36 having a silicon extraction of at least about 20 ppm, an average fiber diameter of less than about 3.5 microns, and a SiO_2 content from about 40-58 wt%.

38. An inorganic fiber according to Claim 37 having a silicon extraction of at least about 50 ppm and an SiO_2 content of from about 40-52 wt% and a MgO content of from about .25-18 wt%.

39. An inorganic fiber having a silicon extraction of at least about 10 ppm over a 5 hour time period in a physiological saline solution and having a composition consisting essentially of about:

(a) 4-6 wt% of material selected from the group consisting of Al_2O_3, ZrO_2, TiO_2, B_2O_3, iron oxides and mixtures thereof;

(b) 40-59 wt% SiO_2;

(c) 0-46 wt% MgO; and

(d) the remainder consisting essentially of CaO, the total being 100 wt%.

40. An inorganic fiber according to Claim 39 having a silicon extraction of at least about 20 ppm, an average fiber diameter of less than about 3.5 microns, and an SiO_2 content from about 40-58 wt%.

41. An inorganic fiber having a diameter of less than about 3.5 microns and which passes the ASTM E-119 two hour fire test when processed into a fiber blanket having a bulk density in the range of about 1.5 to 3 pcf, said inorganic fiber having a composition consisting essentially of:

(a) .06-7 wt% of material selected from the group consisting of Al_2O_3, ZrO_2, TiO_2, B_2O_3, iron oxides and mixtures thereof;

(b) 58-70 wt% SiO_2;

(c) 0-21 wt% MgO;

(d) 0.1-2 wt% alkali metal oxide; and

(e) the remainder consisting essentially of CaO, the total being 100 wt%;

wherein the amount of alumina + zirconia is less than 6 wt% and the amount of iron oxides or alumina + iron oxides is less than 2 wt%.

42. An inorganic fiber according to Claim 41 having a composition consisting essentially of about:

(a) .06-1.5 wt% of material selected from the group consisting of Al_2O_3, ZrO_2, TiO_2, B_2O_3, iron oxides and mixtures thereof; and

(b) 58.5-70 wt% SiO_2.

43. An inorganic fiber according to Claim 42 having a silicon extraction of at least about 10 ppm over a 5 hour period in physiological saline solutions.

44. An inorganic fiber according to Claim 41 having a composition consisting essentially of about:

(a) greater than 1.5 wt% up to and including 3 wt% of material selected from the group consisting of Al_2O_3, ZrO_2, TiO_2, B_2O_3, iron oxides and mixtures thereof; and

(b) 58.5-66 wt% SiO_2.

45. An inorganic fiber according to Claim 44 having a silicon extraction of at least about 10 ppm over a 5 hour period in a physiological saline solution.

46. An inorganic fiber according to Claim 41 having a composition consisting essentially of about:

(a) greater than 3 wt% up to and including 4 wt% material selected from the group consisting of Al_2O_3, ZrO_2, TiO_2, B_2O_3, iron oxides and mixtures thereof;

(b) 58-63 wt% SiO_2;

(c) .25-8 wt% MgO;

(d) .1-2 wt% alkali metal oxide; and

(e) the remainder consisting essentially of CaO, the total being 100 wt%.

47. An inorganic fiber according to Claim 46 having a silicon extraction of at least about 10 ppm over a 5 hour period in physiological saline solutions.

48. An inorganic fiber according to Claim 41 having a composition consisting essentially of about:

(a) greater than 4 wt% up to and including 6 wt% of material selected from the group consisting of Al_2O_3, ZrO_2, TiO_2, B_2O_3, iron oxides and mixtures thereof;

(b) 58-59 wt% SiO_2;

(c) .25-7 wt% MgO;

(d) .1-2 wt% alkali metal oxide; and

(e) the remainder consisting essentially of CaO, the total being 100 wt%.

49. An inorganic fiber according to Claim 48 having a silicon extraction of at least about 10 ppm over a 5 hour period in physiological saline solutions.

50. An inorganic fiber having a silicon extraction of greater than about 0.02 wt% Si/day in a physiological saline solution, a continuous service temperature above about 1450°F and having a composition consisting essentially of about:

(a) .06-5 wt% of material selected from the group consisting of Al_2O_3, ZrO_2, TiO_2, B_2O_3, iron oxides and mixtures thereof;

(b) 40-70 wt% SiO_2;

(c) 0-6 wt% MgO; and

(d) the remainder comprising essentially of CaO, the total being 100 wt%.

51. The fiber of Claim 50 wherein the composition of subsection (c) has an amount of 0.25-6 wt% MgO.

52. An inorganic fiber having a silicon extraction of greater than about 0.02 wt% Si/day in a physiological saline solution, having a continuous service temperature above about 1500°F and having a composition consisting essentially of about:

(a) .06-1.5 wt% of material selected from the group consisting of Al_2O_3, ZrO_2, TiO_2, B_2O_3, iron oxides and mixtures thereof;

(b) 60-70 wt% SiO_2;

(c) 0-1 wt% MgO; and

(d) the remainder consisting essentially of CaO, the total being 100 wt%.

53. The fiber of Claim 52 wherein the composition of subsection (c) has an amount 0.25-1 wt% MgO.

54. An inorganic fiber according to Claims 1 or 29 made from pure oxidic raw materials.

55. An inorganic fiber according to Claim 1 or 29 or 41 in which at least a portion of the raw materials is selected from a group consisting of talc, metallurgical slags, siliceous rocks, kaolin, and mixtures thereof.

56. An inorganic fiber having a composition consisting essentially of about:

(a) 8.0-9.3 wt% Al_2O_3;

(b) 39-52 wt% SiO_2;

(c) 22-38 wt% CaO; and

(d) 7-14 wt% MgO, the total being 100 wt% and having a silica extraction in a saline solution of at least about 5 ppm over a 5 hour period.

57. An inorganic fiber composition having a composition consisting essentially of about:

(a) 49-61 wt% SiO_2;

(b) 10-36 wt% CaO; and

(c) 3-23 wt% MgO, the total being 100 wt% and having a SiO_2 extraction in a saline solution of between about 24-67 ppm over a 5 hour period.

PCT WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification 4 : C03C 13/00, 13/02, 25/06 — A3

(11) International Publication Number: WO 89/12032

(43) International Publication Date: 14 December 1989 (14.12.89)

(21) International Application Number: PCT/US89/02288

(22) International Filing Date: 25 May 1989 (25.05.89)

(30) Priority data:
201,513 1 June 1988 (01.06.88) US

(71) Applicant: MANVILLE SALES CORPORATION [US/US]; Manville Plaza, 5th Floor, P.O. Box 5108, Denver, CO 80217 (US).

(72) Inventors: OLDS, Leonard, Elmo ; 977 South Lake Gulch Road, Castle Rock, CO 80104 (US). KIELMEYER, William, Henry ; 3374 West Chenango Avenue, Englewood, CO 80110 (US).

(74) Agent: SCHRAMM, William, J.; Brooks & Kushman, 2000 Town Center, Suite 2000, Southfield, MI 48075 (US).

(81) Designated States: AT (European patent), AU, BE (European patent), BR, CH (European patent), DE (European patent), DK, FI, FR (European patent), GB (European patent), IT (European patent), JP, KP, KR, LU (European patent), NL (European patent), NO, SE (European patent).

Published
With international search report.
Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.

(88) Date of publication of the international search report:
5 April 1990 (05.04.90)

(54) Title: PROCESS FOR DECOMPOSING AN INORGANIC FIBER

(57) Abstract

Inorganic fibers which have a silicon extraction of greater than 0.02 wt% Si/day in physiological saline solutions. The fiber contains SiO_2, MgO, CaO, and at least one of Al_2O_3, ZrO_2, TiO_2, B_2O_3, iron oxides, or mixtures thereof. Also disclosed are inorganic fibers which have diameters of less than 3.5 microns and which pass the ASTM E-119 two hour fire test when processed into a fiber blanket having a bulk density in the range of about 1.5 to 3 pcf.

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	ES	Spain	MG	Madagascar
AU	Australia	FI	Finland	ML	Mali
BB	Barbados	FR	France	MR	Mauritania
BE	Belgium	GA	Gabon	MW	Malawi
BF	Burkina Fasso	GB	United Kingdom	NL	Netherlands
BG	Bulgaria	HU	Hungary	NO	Norway
BJ	Benin	IT	Italy	RO	Romania
BR	Brazil	JP	Japan	SD	Sudan
CA	Canada	KP	Democratic People's Republic of Korea	SE	Sweden
CF	Central African Republic	KR	Republic of Korea	SN	Senegal
CG	Congo	LI	Liechtenstein	SU	Soviet Union
CH	Switzerland	LK	Sri Lanka	TD	Chad
CM	Cameroon	LU	Luxembourg	TG	Togo
DE	Germany, Federal Republic of	MC	Monaco	US	United States of America
DK	Denmark				

INTERNATIONAL SEARCH REPORT

International Application No PCT/US 89/02288

I. CLASSIFICATION OF SUBJECT MATTER (if several classification symbols apply, indicate all) [6]

According to International Patent Classification (IPC) or to both National Classification and IPC

IPC[4]: C 03 C 13/00, C 03 C 13/02, C 03 C 25/06

II. FIELDS SEARCHED

Minimum Documentation Searched [7]

Classification System	Classification Symbols
IPC[4]	C 03 C

Documentation Searched other than Minimum Documentation to the Extent that such Documents are included in the Fields Searched [8]

III. DOCUMENTS CONSIDERED TO BE RELEVANT [9]

Category [10]	Citation of Document, [11] with indication, where appropriate, of the relevant passages [12]	Relevant to Claim No. [13]
X	WO, A, 87/05007 (MANVILLE CORP.) 27 August 1987 see claim 10; example III; page 5, lines 11-14 --	1-19
A	FR, A, 1165275 (PILKINGTON BROTHERS LTD) 21 October 1958 see claim 1 --	1-15,17-19
A	GB, A, 2083017 (NIPPON SHEET GLASS CO.) 17 March 1982 see claims 1,2; page 5, table 1, samples 9,14; page 2, lines 11-64 --	1-15,17-19
A	GB, A, 1446910 (JAPANA INORGANIC MATERIAL CO.) 18 August 1976 see page 1, lines 22-34 --	1-3,6-15, 17,18
A	US, A, 4366251 (RAPP) 28 December 1982 see claim 1 --	1,3,12-15, 17

./.

* Special categories of cited documents: [10]

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

IV. CERTIFICATION

Date of the Actual Completion of the International Search	Date of Mailing of this International Search Report
1st February 1990	27 FEV. 1990
International Searching Authority	**Signature of Authorized Officer**
EUROPEAN PATENT OFFICE	T.K. WILLIS

International Application No. PCT/US 89/02288

III. DOCUMENTS CONSIDERED TO BE RELEVANT (CONTINUED FROM THE SECOND SHEET)

Category *	Citation of Document, with indication, where appropriate, of the relevant passages	Relevant to Claim No
A	Chemical Abstracts, volume 81, no. 22, 27 November 1978, (Columbus, Ohio, US), see page 285, abstract 184615w, & JP, A, 7856207 (NIPPON SHEET GLASS CO., LTD) 22 May 1978 --	1,3,12-15
X	WO, A, 87/05007 (MANVILLE CORP.) 27 August 1987 see claims 1-10; examples I,II,III; page 5, lines 1-14; page 4, lines 13-21	20-29,50-53
Y		29,41,44-49
A	--	42,43
X	GB, A, 1446910 (JAPAN INORGANIC MATERIAL CO.) 18 August 1976 see page 1, lines 22-34; page 1, line 58 - page 2, line 32	50,51
Y		29,41,44-49
A	--	20-28,42,43,52,53
X	US, A, 2051279 (THORNDYKE) 21 March 1934 see claims 1-4; page 2, right-hand column, lines 16-49; page 2, left-hand column, lines 28-36	50,51
Y		29
A	--	20-28,41-49,52,53
A	US, A, 4366251 (RAPP) 28 December 1982 see claim 1 --	20-22,41
A	GB, A, 2083017 (NIPPON SHEET GLASS CO.) 17 March 1982 see claims 1,2; page 5, table 1, samples 9,14; page 2, lines 11-64 --	20-29,41-49,50-53
A	FR, A, 1165275 (PILKINGTON BROTHERS LTD) 21 October 1958 see claims 1,4 --	20-29,41-49,50-53
A	Chemical Abstracts, volume 81, no. 22, 2 December 1974, (Columbus, Ohio, US), ./..	20-22,41

International Application No. PCT/US 89/02288

FURTHER INFORMATION CONTINUED FROM THE SECOND SHEET

see page 241, abstract 140076b, & SU, A, 409981 (STATE SCIENTIFIC-RESEARCH INSTITUTE OF CONSTRUCTION MATERIALS AND PRODUCTS) 5 January 1974

V. ☐ OBSERVATIONS WHERE CERTAIN CLAIMS WERE FOUND UNSEARCHABLE [1]

This international search report has not been established in respect of certain claims under Article 17(2) (a) for the following reasons:

1. ☐ Claim numbers ....., because they relate to subject matter not required to be searched by this Authority, namely:

2. ☐ Claim numbers ....., because they relate to parts of the international application that do not comply with the prescribed requirements to such an extent that no meaningful international search can be carried out, specifically:

3. ☐ Claim numbers ....., because they are dependent claims and are not drafted in accordance with the second and third sentences of PCT Rule 6.4(a).

VI. ☒ OBSERVATIONS WHERE UNITY OF INVENTION IS LACKING [2]

This International Searching Authority found multiple inventions in this international application as follows:

See Form PCT/ISA/206 dated 29th September 1989.

1. ☐ As all required additional search fees were timely paid by the applicant, this international search report covers all searchable claims of the international application.

2. ☒ As only some of the required additional search fees were timely paid by the applicant, this international search report covers only those claims of the international application for which fees were paid, specifically claims:

1-19,54,55;20-28;29,50-53;41-49

3. ☐ No required additional search fees were timely paid by the applicant. Consequently, this international search report is restricted to the invention first mentioned in the claims; it is covered by claim numbers:

4. ☐ As all searchable claims could be searched without effort justifying an additional fee, the International Searching Authority did not invite payment of any additional fee.

Remark on Protest

☒ The additional search fees were accompanied by applicant's protest.

☐ No protest accompanied the payment of additional search fees.

ANNEX TO THE INTERNATIONAL SEARCH REPORT ON INTERNATIONAL PATENT APPLICATION NO. US 8902288 SA 29321

This annex lists the patent family members relating to the patent documents cited in the above-mentioned international search report. The members are as contained in the European Patent Office EDP file on 21/02/90
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO-A- 8705007	27-08-87	AU-A- 6948887	09-09-87
		EP-A- 0257092	02-03-88
		JP-T- 63502746	13-10-88
FR-A- 1165275		CH-A- 360770	
		GB-A- 810773	
GB-A- 2083017	17-03-82	JP-A- 57047741	18-03-82
		US-A- 4443550	17-04-84
GB-A- 1446910	18-08-76	JP-A- 50014820	17-02-75
		AU-A- 5892673	06-02-75
		CA-A- 1022195	06-12-77
		US-A- 4038089	26-07-77
US-A- 4366251	28-12-82	None	
WO-A- 8705007	27-08-87	AU-A- 6948887	09-09-87
		EP-A- 0257092	02-03-88
		JP-T- 63502746	13-10-88
GB-A- 1446910	18-08-76	JP-A- 50014820	17-02-75
		AU-A- 5892673	06-02-75
		CA-A- 1022195	06-12-77
		US-A- 4038089	26-07-77
US-A- 2051279		None	
US-A- 4366251	28-12-82	None	
GB-A- 2083017	17-03-82	JP-A- 57047741	18-03-82
		US-A- 4443550	17-04-84
FR-A- 1165275		CH-A- 360770	
		GB-A- 810773	

PCT WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification 4 : C03C 13/00, 13/02, 25/06	A3	(11) International Publication Number: WO 89/12032
		(43) International Publication Date: 14 December 1989 (14.12.89)

(21) International Application Number: PCT/US89/02288

(22) International Filing Date: 25 May 1989 (25.05.89)

(30) Priority data:
201,513 1 June 1988 (01.06.88) US

(71) Applicant: MANVILLE SALES CORPORATION [US/US]; Manville Plaza, 5th Floor, P.O. Box 5108, Denver, CO 80217 (US).

(72) Inventors: OLDS, Leonard, Elmo ; 977 South Lake Gulch Road, Castle Rock, CO 80104 (US). KIELMEYER, William, Henry ; 3374 West Chenango Avenue, Englewood, CO 80110 (US).

(74) Agent: SCHRAMM, William, J.; Brooks & Kushman, 2000 Town Center, Suite 2000, Southfield, MI 48075 (US).

(81) Designated States: AT (European patent), AU, BE (European patent), BR, CH (European patent), DE (European patent), DK, FI, FR (European patent), GB (European patent), IT (European patent), JP, KP, KR, LU (European patent), NL (European patent), NO, SE (European patent).

Published
With international search report.
Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.

(88) Date of publication of the international search report:
5 April 1990 (05.04.90)

(54) Title: PROCESS FOR DECOMPOSING AN INORGANIC FIBER

(57) Abstract

Inorganic fibers which have a silicon extraction of greater than 0.02 wt% Si/day in physiological saline solutions. The fiber contains SiO_2, MgO, CaO, and at least one of Al_2O_3, ZrO_2, TiO_2, B_2O_3, iron oxides, or mixtures thereof. Also disclosed are inorganic fibers which have diameters of less than 3.5 microns and which pass the ASTM E-119 two hour fire test when processed into a fiber blanket having a bulk density in the range of about 1.5 to 3 pcf.

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	FI	Finland	ML	Mali
AU	Australia	FR	France	MR	Mauritania
BB	Barbados	GA	Gabon	MW	Malawi
BE	Belgium	GB	United Kingdom	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IT	Italy	RO	Romania
BJ	Benin	JP	Japan	SD	Sudan
BR	Brazil	KP	Democratic People's Republic of Korea	SE	Sweden
CF	Central African Republic			SN	Senegal
CG	Congo	KR	Republic of Korea	SU	Soviet Union
CH	Switzerland	LI	Liechtenstein	TD	Chad
CM	Cameroon	LK	Sri Lanka	TG	Togo
DE	Germany, Federal Republic of	LU	Luxembourg	US	United States of America
DK	Denmark	MC	Monaco		
ES	Spain	MG	Madagascar		

INTERNATIONAL SEARCH REPORT

International Application No PCT/US 89/02288

I. CLASSIFICATION OF SUBJECT MATTER (if several classification symbols apply, indicate all) [6]

According to International Patent Classification (IPC) or to both National Classification and IPC

IPC[4]: C 03 C 13/00, C 03 C 13/02, C 03 C 25/06

II. FIELDS SEARCHED

Minimum Documentation Searched [7]

Classification System	Classification Symbols
IPC[4]	C 03 C

Documentation Searched other than Minimum Documentation to the Extent that such Documents are included in the Fields Searched [8]

III. DOCUMENTS CONSIDERED TO BE RELEVANT [9]

Category [10]	Citation of Document, [11] with indication, where appropriate, of the relevant passages [12]	Relevant to Claim No. [13]
X	WO, A, 87/05007 (MANVILLE CORP.) 27 August 1987 see claim 10; example III; page 5, lines 11-14 --	1-19
A	FR, A, 1165275 (PILKINGTON BROTHERS LTD) 21 October 1958 see claim 1 --	1-15,17-19
A	GB, A, 2083017 (NIPPON SHEET GLASS CO.) 17 March 1982 see claims 1,2; page 5, table 1, samples 9,14; page 2, lines 11-64 --	1-15,17-19
A	GB, A, 1446910 (JAPANA INORGANIC MATERIAL CO.) 18 August 1976 see page 1, lines 22-34 --	1-3,6-15, 17,18
A	US, A, 4366251 (RAPP) 28 December 1982 see claim 1 --	1,3,12-15, 17

./.

* Special categories of cited documents: [10]

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

IV. CERTIFICATION

Date of the Actual Completion of the International Search	Date of Mailing of this International Search Report
1st February 1990	27 FEV. 1990
International Searching Authority	**Signature of Authorized Officer**
EUROPEAN PATENT OFFICE	T.K. WILLIS

International Application No. PCT/US 89/02288

III. DOCUMENTS CONSIDERED TO BE RELEVANT (CONTINUED FROM THE SECOND SHEET)

Category *	Citation of Document, with indication, where appropriate, of the relevant passages	Relevant to Claim No
A	Chemical Abstracts, volume 81, no. 22, 27 November 1978, (Columbus, Ohio, US), see page 285, abstract 184615w, & JP, A, 7856207 (NIPPON SHEET GLASS CO., LTD) 22 May 1978 --	1,3,12-15
X	WO, A, 87/05007 (MANVILLE CORP.) 27 August 1987 see claims 1-10; examples I,II,III; page 5, lines 1-14; page 4, lines 13-21	20-29,50-53
Y		29,41,44-49
A		42,43
	--	
X	GB, A, 1446910 (JAPAN INORGANIC MATERIAL CO.) 18 August 1976 see page 1, lines 22-34; page 1, line 58 - page 2, line 32	50,51
Y		29,41,44-49
A		20-28,42,43,52,53
	--	
X	US, A, 2051279 (THORNDYKE) 21 March 1934 see claims 1-4; page 2, right-hand column, lines 16-49; page 2, left-hand column, lines 28-36	50,51
Y		29
A		20-28,41-49,52,53
	--	
A	US, A, 4366251 (RAPP) 28 December 1982 see claim 1	20-22,41
	--	
A	GB, A, 2083017 (NIPPON SHEET GLASS CO.) 17 March 1982 see claims 1,2; page 5, table 1, samples 9,14; page 2, lines 11-64	20-29,41-49,50-53
	--	
A	FR, A, 1165275 (PILKINGTON BROTHERS LTD) 21 October 1958 see claims 1,4	20-29,41-49,50-53
	--	
A	Chemical Abstracts, volume 81, no. 22, 2 December 1974, (Columbus, Ohio, US), ./..	20-22,41

International Application No. PCT/US 89/02288

FURTHER INFORMATION CONTINUED FROM THE SECOND SHEET

see page 241, abstract 140076b, & SU, A, 409981 (STATE SCIENTIFIC-RESEARCH INSTITUTE OF CONSTRUCTION MATERIALS AND PRODUCTS) 5 January 1974

V. ☐ OBSERVATIONS WHERE CERTAIN CLAIMS WERE FOUND UNSEARCHABLE [1]

This international search report has not been established in respect of certain claims under Article 17(2) (a) for the following reasons:

1. ☐ Claim numbers ..... because they relate to subject matter not required to be searched by this Authority, namely:

2. ☐ Claim numbers ....., because they relate to parts of the international application that do not comply with the prescribed requirements to such an extent that no meaningful international search can be carried out, specifically:

3. ☐ Claim numbers ....., because they are dependent claims and are not drafted in accordance with the second and third sentences of PCT Rule 6.4(a).

VI. ☒ OBSERVATIONS WHERE UNITY OF INVENTION IS LACKING [2]

This International Searching Authority found multiple inventions in this international application as follows:

See Form PCT/ISA/206 dated 29th September 1989.

1. ☐ As all required additional search fees were timely paid by the applicant, this international search report covers all searchable claims of the international application.

2. ☒ As only some of the required additional search fees were timely paid by the applicant, this international search report covers only those claims of the international application for which fees were paid, specifically claims:

1-19,54,55;20-28;29,50-53;41-49

3. ☐ No required additional search fees were timely paid by the applicant. Consequently, this international search report is restricted to the invention first mentioned in the claims; it is covered by claim numbers:

4. ☐ As all searchable claims could be searched without effort justifying an additional fee, the International Searching Authority did not invite payment of any additional fee.

Remark on Protest

☒ The additional search fees were accompanied by applicant's protest.

☐ No protest accompanied the payment of additional search fees.

ANNEX TO THE INTERNATIONAL SEARCH REPORT ON INTERNATIONAL PATENT APPLICATION NO. US 8902288 SA 29321

This annex lists the patent family members relating to the patent documents cited in the above-mentioned international search report. The members are as contained in the European Patent Office EDP file on 21/02/90 The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO-A- 8705007	27-08-87	AU-A- 6948887	09-09-87
		EP-A- 0257092	02-03-88
		JP-T- 63502746	13-10-88
FR-A- 1165275		CH-A- 360770	
		GB-A- 810773	
GB-A- 2083017	17-03-82	JP-A- 57047741	18-03-82
		US-A- 4443550	17-04-84
GB-A- 1446910	18-08-76	JP-A- 50014820	17-02-75
		AU-A- 5892673	06-02-75
		CA-A- 1022195	06-12-77
		US-A- 4038089	26-07-77
US-A- 4366251	28-12-82	None	
WO-A- 8705007	27-08-87	AU-A- 6948887	09-09-87
		EP-A- 0257092	02-03-88
		JP-T- 63502746	13-10-88
GB-A- 1446910	18-08-76	JP-A- 50014820	17-02-75
		AU-A- 5892673	06-02-75
		CA-A- 1022195	06-12-77
		US-A- 4038089	26-07-77
US-A- 2051279		None	
US-A- 4366251	28-12-82	None	
GB-A- 2083017	17-03-82	JP-A- 57047741	18-03-82
		US-A- 4443550	17-04-84
FR-A- 1165275		CH-A- 360770	
		GB-A- 810773	